



EMSL Analytical, Inc.

2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906702

Fax: (318) 687-9923 Phone: (318) 687-3771
Project: **09-16368, Olin E. Teague VAMC Reinspection**

EMSL Proj: Waco/Temple VA
Analysis Date: 12/11/2009

Test Report: Asbestos Analysis of Bulk Material via EPA 600/R-93/116. Quantitation using 400 Point Count Procedure.


Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
OT-09-293-0464 260906702-0080	Bldg. 162	White Non-Fibrous Heterogeneous		97.00% Non-fibrous (other)	3.00% Amosite
OT-09-293-0472 260906702-0081	Bldg. 162	White Non-Fibrous Heterogeneous		96.75% Non-fibrous (other)	3.25% Amosite <0.25% Chrysotile
OT-09-293-0477 260906702-0082	Bldg. 162	White Non-Fibrous Heterogeneous		98.75% Non-fibrous (other)	1.25% Amosite <0.25% Chrysotile
OT-09-293-0482 260906702-0083	Bldg. 162	White Non-Fibrous Heterogeneous		98.75% Non-fibrous (other)	1.25% Amosite <0.25% Chrysotile
OT-09-293-0484 260906702-0084	Bldg. 162	White Non-Fibrous Heterogeneous		98.50% Non-fibrous (other)	1.50% Amosite <0.25% Chrysotile
OT-09-293-0486 260906702-0085	Bldg. 162	White Non-Fibrous Heterogeneous		98.25% Non-fibrous (other)	1.75% Amosite <0.25% Chrysotile
OT-09-293-0491 260906702-0086	Bldg. 162	White Non-Fibrous Heterogeneous		98.00% Non-fibrous (other)	1.75% Amosite 0.25% Chrysotile
OT-09-293-0493 260906702-0087	Bldg. 162	White Non-Fibrous Heterogeneous		98.50% Non-fibrous (other)	1.50% Amosite <0.25% Chrysotile

Analyst(s)

Michael Pohlmann (8)

Andrei Poluchowicz,
or other approved signatory

Disclaimer: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval of EMSL Analytical Inc. This test report must not be used by the client to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc., bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layered samples. EMSL Analytical Inc., liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL NVLAP Lab Code 200399-0, TX 300289



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906702

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: 09-16368, Olin E. Teague VAMC Reinspection

EMSL Proj: Waco/Temple VA
 Analysis Date: 12/11/2009

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(%) Matrix Organic Acid	ASBESTOS % TYPES	NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
OT-09-293-0468 Mastic 260906702-0077	Bldg. 162					
Insufficient Material						
Insufficient Material						
OT-09-293-0473 Floor Tile 260906702-0078	Bldg. 162	Brown Non-Fibrous Homogeneous	24.3	61.7 <0.25 Chrysotile		13.9 Non-fibrous (other)
OT-09-293-0473 Mastic 260906702-0079	Bldg. 162					
Insufficient Material						
Insufficient Material						

Analyst(s)

Michael Pohlmann (5)

Andrei Poluchowicz,
 or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
 Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906702
 EMSL Proj: Waco/Temple VA
 Analysis Date: 12/22/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: 09-16368, Olin E. Teague VAMC Reinspection

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(%) Matrix Organic Acid		ASBESTOS % TYPES		NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
OT-09-293-0468 Mastic 260906702-0077	Bldg. 162	Black Non-Fibrous Homogeneous	56.5	16.8	0.9	Chrysotile		25.8 Non-fibrous (other)
OT-09-293-0473 Floor Tile 260906702-0078	Bldg. 162	Brown Non-Fibrous Homogeneous	24.3	61.7	<0.25	Chrysotile		13.9 Non-fibrous (other)
OT-09-293-0473 Mastic 260906702-0079	Bldg. 162	Black Non-Fibrous Homogeneous	67.1	18.5	1.5	Chrysotile		12.9 Non-fibrous (other)

12/23/09; Insufficient samples were resampled, analyzed at client client request.

Report Amended: 12/23/2009 7:23:09 AM Replaces the Inital Report . Reason Code: Data Entry-Results Changed

Analyst(s)

Jonathan Tallert (6)
 Michael Pohlmann (5)

Andrei Poluchowicz,
 or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc.. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
 Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicago@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906723
 EMSL Proj: Waco/Temple VA
 Analysis Date: 12/10/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: 09-16368, Olin E. Teague VAMC Reinspection

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(%) Matrix Organic Acid	ASBESTOS % TYPES	NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
OT-09-293-0496 Floor Tile 2 260906723-0054	Bldg. 162	Gray Non-Fibrous Homogeneous	15.0	73.4 <0.25 Chrysotile		11.6 Non-fibrous (other)
OT-09-293-Mastic 260906723-0055	Bldg. 162	Insufficient Material				
Insufficient Material						
OT-09-293-0710 Mastic 260906723-0056	Bldg. 162	Black Non-Fibrous Homogeneous	58.9	7.5 0.6 Chrysotile		33.1 Non-fibrous (other)

Analyst(s)

 Alice Hillegass (4)

Andrei Poluchowicz,
 or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
 Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL.



EMSL Analytical, Inc.

2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906723

Fax: (318) 687-9923 Phone: (318) 687-3771
Project: **09-16368, Olin E. Teague VAMC Reinspection**

EMSL Proj: Waco/Temple VA
Analysis Date: 12/10/2009

Test Report: Asbestos Analysis of Bulk Material via EPA 600/R-93/116. Quantitation using 400 Point Count Procedure.


Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
OT-09-293-0706 <i>260906723-0057</i>	Bldg. 162	White Non-Fibrous Homogeneous		98.75% Non-fibrous (other)	1.25% Chrysotile
OT-09-293-0711 <i>260906723-0058</i>	Bldg. 162	White Non-Fibrous Homogeneous		97.75% Non-fibrous (other)	1.50% Amosite 0.75% Chrysotile
OT-09-293-0713 Insulation <i>260906723-0059</i>	Bldg. 162	White Non-Fibrous Homogeneous		98.00% Non-fibrous (other)	1.25% Amosite 0.75% Chrysotile

Analyst(s) _____
Alice Hillegass (3)



Andrei Poluchowicz,
or other approved signatory

Disclaimer: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval of EMSL Analytical Inc. This test report must not be used by the client to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc., bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layered samples. EMSL Analytical Inc., liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL NVLAP Lab Code 200399-0, TX 300289



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906788

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: 09-16368; Olin E. Teague VAC Reinspection

EMSL Proj: Waco/Temple VA
 Analysis Date: 12/14/2009

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(%) Matrix Organic Acid	ASBESTOS % TYPES	NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
OT-09-293-0724 Floor Tile 260906788-0059	Bldg. 162	Brown Non-Fibrous Homogeneous	22.7	67.4 <0.25 Chrysotile		10.0 Non-fibrous (other)
OT-09-293-0724 Mastic 260906788-0060	Bldg. 162	Black Non-Fibrous Homogeneous	58.3	24.9 0.9 Chrysotile		16.0 Non-fibrous (other)

Analyst(s)

Michael Pohlmann (7)

Andrei Poluchowicz,
 or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
 Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicago@emsl.com


Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906788
 EMSL Proj: Waco/Temple VA
 Analysis Date: 12/14/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: **09-16368; Olin E. Teague VAC Reinspection**

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(% Matrix Organic Acid)		ASBESTOS % TYPES		NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
OT-09-293-0741 Mastic 1 260906788-0061	Bldg. 162				Insufficient Material			
Insufficient Material								
OT-09-293-0743 Mastic 260906788-0062	Bldg. 162	Black/Yellow Non-Fibrous Heterogeneous	75.6	17.8	0.5	Chrysotile		6.2 Non-fibrous (other)
OT-09-293-0751 260906788-0063	Bldg. 162	Black Non-Fibrous Homogeneous	91.2	2.2	0.4	Chrysotile		6.1 Non-fibrous (other)



Analyst(s)

Michael Pohlmann (7)

Andrei Poluchowicz,
 or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.
2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicago@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906788
EMSL Proj: Waco/Temple VA
Analysis Date: 12/22/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
Project: **09-16368; Olin E. Teague VAC Reinspection**

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(% Matrix Organic Acid)		ASBESTOS % TYPES	NON-ASBESTOS % Fibrous	NON-ASBESTOS % NON-FIBROUS
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]	[REDACTED]
OT-09-293-0724 Floor Tile 260906788-0059	Bldg. 162	Brown Non-Fibrous Homogeneous	22.7	67.4	<0.25	Chrysotile	10.0 Non-fibrous (other)
OT-09-293-0724 Mastic 260906788-0060	Bldg. 162	Black Non-Fibrous Homogeneous	58.3	24.9	0.9	Chrysotile	16.0 Non-fibrous (other)

Report Amended: 12/23/2009 7:32:10 AM Replaces the Inital Report . Reason Code: Data Entry-Results Changed


Analyst(s)

Alice Hillegass (4)
Michael Pohlmann (7)



Andrei Poluchowicz,
or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.
Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.

2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906788

EMSL Proj: Waco/Temple VA
Analysis Date: 12/22/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
Project: **09-16368; Olin E. Teague VAC Reinspection**

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

SAMPLE ID	DESCRIPTION	APPEARANCE	(% Matrix Organic Acid		ASBESTOS % TYPES		NON- ASBESTOS % Fibrous	NON- ASBESTOS % NON-FIBROUS
OT-09-293-0741 Mastic 1 260906788-0061	Bldg. 162	Black Non-Fibrous Homogeneous	54.0	17.1	3.3	Chrysotile		25.6 Non-fibrous (other)
OT-09-293-0743 Mastic 260906788-0062	Bldg. 162	Black/Yellow Non-Fibrous Heterogeneous	75.6	17.8	0.5	Chrysotile		6.2 Non-fibrous (other)
OT-09-293-0751 260906788-0063	Bldg. 162	Black Non-Fibrous Homogeneous	91.2	2.2	0.4	Chrysotile		6.1 Non-fibrous (other)



12/23/09; insufficient samples resampled, analyzed at client request.


Report Amended: 12/23/2009 7:32:10 AM Replaces the Inital Report . Reason Code: Data Entry-Results Changed

Analyst(s)

Alice Hillegass (4)
Michael Pohlmann (7)

Andrei Poluchowicz,
or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc.. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted. Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL.



EMSL Analytical, Inc.
 2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicago@emsl.com

Attn: **Roy W. Dowling**
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT 50
 Customer PO:
 Received: 12/07/09 3:30 PM
 EMSL Order: 260906788
 EMSL Proj: Waco/Temple VA
 Analysis Date: 12/14/2009

Fax: (318) 687-9923 Phone: (318) 687-3771
 Project: **09-16368; Olin E. Teague VAC Reinspection**

Test Report: Asbestos Analysis of Bulk Material via EPA 600/R-93/116. Quantitation using 400 Point Count Procedure.

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
[REDACTED]					
OT-09-293-0736 260906788-0066	Bldg. 162	White Non-Fibrous Homogeneous		92.00% Non-fibrous (other)	8.00% Chrysotile
OT-09-293-0746 260906788-0067	Bldg. 162	White Non-Fibrous Heterogeneous		98.00% Non-fibrous (other)	2.00% Amosite <0.25% Chrysotile

Analyst(s)

Michael Pohlmann (3)

Andrei Poluchowicz,
 or other approved signatory

Disclaimer: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval of EMSL Analytical Inc. This test report must not be used by the client to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc., bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layered samples. EMSL Analytical Inc., liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL NVLAP Lab Code 200399-0, TX 300269



EMSL Analytical, Inc.

2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicago@emsl.com

Attn: Roy W. Dowling
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Fax: (318) 687-9923 Phone: (318) 687-3771
Project: Olin E. Teague VAMC Reinspection

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906816
EMSL Proj: Waco/Temple VA
Analysis Date: 12/10/2009

Test Report: Polarized Light Microscopy (PLM) - Point Count Performed by EPA 600/R-93/116 Method with Gravimetric Reduction and 400 Point Count

Table with 7 columns: SAMPLE ID, DESCRIPTION, APPEARANCE, (% Matrix Organic Acid), ASBESTOS % TYPES, NON-ASBESTOS % Fibrous, NON-ASBESTOS % NON-FIBROUS. Rows include samples like OT-09-293-0755 Mastic, OT-09-293-0760 Floor Tile, etc.

Analyst(s)

Alice Hillegass (6)

Handwritten signature of Andrei Poluchowicz

Andrei Poluchowicz, or other approved signatory

Disclaimers: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc. suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval by EMSL Analytical Inc. This report must not be used to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc. bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layer samples. EMSL Analytical Inc. liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted. Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL



EMSL Analytical, Inc.

2444 W. George Street, Chicago, IL 60618

Phone: (773) 313-0099 Fax: (773) 313-0139 Email: chicagolab@emsl.com

Attn: Roy W. Dowling
ALTEC Environmental Consultants, Inc.
P.O. Box 17867
Shreveport, LA 71138-0867

Customer ID: ALT50
Customer PO:
Received: 12/07/09 3:30 PM
EMSL Order: 260906816

Fax: (318) 687-9923 Phone: (318) 687-3771

EMSL Proj: Waco/Temple VA
Analysis Date: 12/10/2009

Project: Olin E. Teague VAMC Reinspection

Test Report: Asbestos Analysis of Bulk Material via EPA 600/R-93/116. Quantitation using 400 Point Count Procedure.

Table with 7 columns: Sample, Description, Appearance, % Fibrous, % Non-Fibrous, % Type. Contains 5 rows of data with varying asbestos percentages and types like Chrysotile, Amosite.

Analyst(s)

Alice Hillegass (4)

Handwritten signature of Andrei Poluchowicz

Andrei Poluchowicz, or other approved signatory

Disclaimer: Some samples may contain asbestos fibers present in dimensions below PLM resolution limits. The limit of detection as stated in the method is 0.25%. EMSL Analytical Inc suggests that samples reported as <0.25% or none detected undergo additional analysis via TEM. The above test report relates only to the items tested. This report may not be reproduced, except in full, without written approval of EMSL Analytical Inc. This test report must not be used by the client to claim product endorsement by NVLAP or any agency of the United States Government. EMSL Analytical Inc., bears no responsibility for sample collection activities, analytical method limitations, or the accuracy of results when requested to separate layered samples. EMSL Analytical Inc., liability is limited to the cost of sample analysis. The test results contained within this report meet the requirements of NELAC unless otherwise noted. Samples received in good condition unless otherwise noted.

Samples analyzed by EMSL Analytical, Inc. Chicago 2444 W. George Street, Chicago IL NVLAP Lab Code 200399-0, TX 300289

CERTIFICATIONS

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

BRANDON ODOM

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0101392

AI No. 149011

Date of Issuance 2/13/2009

Expiration 2/7/2010

Failure to comply with all applicable provisions of La. R.S. 2025F (1)(a) and La. R.S. 2025F (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Nathan Levey

Permit Support Services Division
Office of Environmental Services

LOUISIANA

ALTEC TRAINING SERVICES

This is to certify that

BRANDON ODOM

has successfully completed the required 4 hours of refresher training

under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for

Asbestos Inspector

as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)

on January 21, 2009, in Keithville, Louisiana.

Certificate Number: 09021IR009384488

Accreditation expires: January 21, 2010

Examination date: N/A



Roy W. Dowling, Training Manager
DEQ Certification No. A09T0286

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

GRAY CHASE

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0I01035

AI No. 129416

Date of Issuance 8/21/2009

Expiration 9/9/2010

Failure to comply with all applicable provisions of La. R.S. 2025.E. (1)(a) and La. R.S. 2025.F. (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Jodi S. Miller

Permit Support Services Division
Office of Environmental Services

ALTEC TRAINING SERVICES

This is to certify that

GRAY CHASE

has successfully completed the required 4 hours of refresher training

under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for

Asbestos Inspector


as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)

on August 7, 2009, in Keithville, Louisiana.

Certificate Number: 09219IR-001 LA008946840

Accreditation expires: August 7, 2010

Examination date: N/A



Roy W. Dowling, Training Manager
DEQ Certification No. A09T0286

ALTEC Environmental Consultants, Inc. ♦ P.O. Box 17867 ♦ Shreveport, Louisiana 71138-0867 ♦ (318) 687-3771

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

JUSTIN L HOLCOMB

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0I00306

AI No. 112785

Date of Issuance 5/13/2009

Expiration 5/22/2010

Failure to comply with all applicable provisions of La. R.S. 2025:1, (1)(a) and La. R.S. 2025:1, (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Justin M. Miller

Permit Support Services Division
Office of Environmental Services

LOUISIANA

ALTEC TRAINING SERVICES

This is to certify that

JUSTIN L. HOLCOMB

*has successfully completed the required 4 hours of refresher training
under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for*

Asbestos Inspector

*as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)
on May 1, 2009, in Keithville, Louisiana.*

Certificate Number: 09121IR006764980

Accreditation expires: May 1, 2010

Examination date: N/A



Roy W. Dowling, Training Manager
DEQ Certification No. A09T0286

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

DONALD R JOINER

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0I01348

AI No. 112937

Date of Issuance 8/21/2009

Expiration 9/29/2010

Failure to comply with all applicable provisions of La. R.S. 2025.E. (1)(a) and La. R.S. 2025.F. (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Jodi S. Miller

Permit Support Services Division
Office of Environmental Services

ALTEC TRAINING SERVICES

This is to certify that

DONALD JOINER

has successfully completed the required 4 hours of refresher training

under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for

Asbestos Inspector


as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)

on August 7, 2009, in Keithville, Louisiana.

Certificate Number: 09219IR-002 LA003036858

Accreditation expires: August 7, 2010

Examination date: N/A



Roy W. Dowling, Training Manager
DEQ Certification No. A09T0286

ALTEC Environmental Consultants, Inc. ♦ P.O. Box 17867 ♦ Shreveport, Louisiana 71138-0867 ♦ (318) 687-3771

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

JERALD HEIDECKER

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0101698

AI No. 166471

Date of Issuance 10/15/2009

Expiration 9/25/2010

Failure to comply with all applicable provisions of La. R.S. 2025.E. (1)(a) and La. R.S. 2025.F. (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Jodi B. Miller

Permit Support Services Division
Office of Environmental Services

ALTEC TRAINING SERVICES

This is to certify that

JERRY HEIDECKER

*has successfully completed the required 24 hours of initial training
under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for*

Asbestos Inspector

*as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)
on September 23 – September 25, 2009, in Keithville, Louisiana.*

**Certificate Number: 09268I-001 LA003327701
Accreditation expires: September 25, 2010
Examination date: September 25, 2009**



Roy W. Dowling, Training Manager
DEQ Certification No. A10T0286

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

BRANDON L SANDERS

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0I01097

AI No. 114549

Date of Issuance 10/12/2009

Expiration 9/25/2010

Failure to comply with all applicable provisions of La. R.S. 2025.E. (1)(a) and La. R.S. 2025.F. (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Jodi H. Miller

Permit Support Services Division
Office of Environmental Services

ALTEC TRAINING SERVICES

This is to certify that

BRANDON SANDERS

has successfully completed the required 24 hours of initial training

under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for

Asbestos Inspector


as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)

on September 23 – September 25, 2009, in Keithville, Louisiana.

Certificate Number: 09268I-002 LA005671200

Accreditation expires: September 25, 2010

Examination date: September 25, 2009



Roy W. Dowling, Training Manager

DEQ Certification No. A10T0286

ALTEC Environmental Consultants, Inc. ♦ P.O. Box 17867 ♦ Shreveport, Louisiana 71138-0867 ♦ (318) 687-3771

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

ROY W DOWLING

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS INSPECTOR

Accreditation No. 0100213

AI No. 94796

Date of Issuance 5/13/2009

Expiration 6/26/2010

Failure to comply with all applicable provisions of La. R.S. 2025.F. (1)(a) and La. R.S. 2025.J. (2)(a)
may result in civil and/or criminal enforcement actions by the state.

John H. Miller

Permit Support Services Division
Office of Environmental Services

LOUISIANA

ALTEC TRAINING SERVICES

This is to certify that

ROY W. DOWLING

*has successfully completed the required 4 hours of refresher training
under Section 206 of TSCA, Title II, 15 U.S.C. 2646, for*

Asbestos Inspector


as approved by the State of Louisiana and U.S.E.P.A. under 40 CFR 763 (AHERA)

on May 1, 2009, in Keithville, Louisiana.

Certificate Number: 09121IR004572291

Accreditation expires: May 1, 2010

Examination date: N/A



**Gray Chase, Instructor
DEQ Certification No. A10T0013**

STATE OF LOUISIANA
DEPARTMENT OF ENVIRONMENTAL QUALITY

certifies that

ROY W DOWLING

Has complied with all requirements of the Louisiana Department of Environmental Quality
and is authorized to perform the duties of

ASBESTOS MANAGEMENT PLANNER

Accreditation No. 0P00072

AI No. 94796

Date of Issuance 8/12/2009

Expiration 10/3/2010

Failure to comply with all applicable provisions of La. R.S. 2025.E. (1)(a) and La. R.S. 2025.F. (2)(a)
may result in civil and/or criminal enforcement actions by the State.

Jodi H. Miller

Permit Support Services Division
Office of Environmental Services



TEXAS DEPARTMENT OF STATE HEALTH SERVICES

EMSL ANALYTICAL, INC

is certified to perform as a

Asbestos Laboratory PCM, PLM, TEM

in the State of Texas within the purview of Texas Occupations Code, chapter 1954, so long as this license is not suspended or revoked and is renewed according to the rules adopted by the Texas Board of Health.

A handwritten signature in cursive script, reading "David Lakey, M.D.".

DAVID LAKEY, M.D.
COMMISSIONER OF HEALTH

License Number: 300289

Control Number: 95498

Expiration Date: 5/7/2010

(Void After Expiration Date)

VOID IF ALTERED NON-TRANSFERABLE

PERIODIC SURVEILLANCE FORMS

TEMPLE VA MEDICAL CENTER
6-MONTH ASBESTOS SURVEILLANCE

BUILDING 162

HMA	Material Description	Location	Friable Yes/No	Conditions at Last Inspection ¹	Damage Severity ²	Conditions at Current Inspection ¹	Comments
HMA-01	9x9 Floor Tile and Mastic	First Floor - Northwest					
HMA-02	Flooring Mastic	First Floor - Northwest					
HMA-04	Pipe Insulation and Fittings	First Floor - Northwest					
HMA-05	Sink Undercoating	First Floor - Northwest					
HMA-02	Flooring Mastic	First Floor - Northeast					
HMA-04	Pipe Insulation and Fittings	First Floor - Northeast					
HMA-05	Sink Undercoating	First Floor - Northeast					
HMA-06	Transite Vent Hood	First Floor - Northeast					
HMA-07	Sink Backsplash	First Floor - Northeast					
HMA-02	Flooring Mastic	First Floor - Southwest					
HMA-04	Pipe Insulation and Fittings	First Floor - Southwest					
HMA-05	Sink Undercoating	First Floor - Southwest					
HMA-02	Flooring Mastic	First Floor - Southeast					
HMA-03	12x12 Floor Tile and Mastic	First Floor - Southeast					