

**EMSL Analytical, Inc.**

1010 Yuma Street, Denver, CO 80204

Phone/Fax: (303) 740-5700 / (303) 741-1400

<http://www.EMSL.com>denverlab@emsl.com

EMSL Order:	221501681
CustomerID:	GJMC34
CustomerPO:	
ProjectID:	

Attn: Dennis Allen Grand Junction VA Medical Center 2121 North Avenue Grand Junction, CO 81501	Phone: (970) 242-0731 Fax: Received: 03/30/15 9:36 AM Analysis Date: 3/30/2015 Collected:
Project: Dietetics Renovation	

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
3224-White Plaster 221501681-0001	B1/RM 3224 Dietetics	White Non-Fibrous Homogeneous		15% Quartz 85% Non-fibrous (other)	<1% Chrysotile
3224-Tan Plaster 221501681-0001A	B1/RM 3224 Dietetics	Tan Non-Fibrous Homogeneous		15% Quartz 10% Ca Carbonate 75% Non-fibrous (other)	<1% Chrysotile
3226 221501681-0002	B1/ RM 3226	Tan Non-Fibrous Homogeneous		15% Quartz 10% Ca Carbonate 75% Non-fibrous (other)	None Detected

*Received
3/30/15
DA*

Analyst(s)
Brian Shelton (3)

Barbara Shepherd
Barbara Shepherd, Laboratory Manager
or other approved signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%
Samples analyzed by EMSL Analytical, Inc. Denver, CO NVLAP Lab Code 200828-0

Initial report from 03/30/2015 13:39:26