

**EMSL Analytical, Inc**

464 McCormick Street, San Leandro, CA 94577

Phone/Fax: (510) 895-3675 / (510) 895-3680

<http://www.EMSL.com>sanleandrolab@emsl.com

EMSL Order: 091506198

CustomerID: MECA62

CustomerPO: 9667

ProjectID:

Attn: **Jenice Feiner**
Millennium Consulting Associates, Inc.
401 Roland Way
Suite 250
Oakland, CA 94621

Phone: (925) 808-6700
Fax: (925) 808-6708
Received: 04/30/15 5:45 PM
Analysis Date: 5/1/2015
Collected: 4/30/2015

Project: 18034.2049 VA MENO PARK

Test Report: Asbestos Analysis of Bulk Materials via EPA 600/R-93/116 Method using Polarized Light Microscopy

Sample	Description	Appearance	Non-Asbestos		Asbestos
			% Fibrous	% Non-Fibrous	% Type
150430-14.1-Stucco 091506198-0001	N. EXTERIOR F WING	Gray/White Non-Fibrous Homogeneous		40% Quartz 60% Non-fibrous (other)	None Detected
150430-14.2-Stucco 091506198-0002	C WING EXT. NE	Gray/White Non-Fibrous Homogeneous		40% Quartz 60% Non-fibrous (other)	None Detected
150430-14.3-Stucco 091506198-0003	E. D- WING EXTERIOR	Gray/White Non-Fibrous Homogeneous		40% Quartz 60% Non-fibrous (other)	None Detected

Analyst(s)

Alexander Shmurakov (3)

Chris Dojlidko, Laboratory Manager
or other approved signatory

EMSL maintains liability limited to cost of analysis. This report relates only to the samples reported and may not be reproduced, except in full, without written approval by EMSL. EMSL bears no responsibility for sample collection activities or analytical method limitations. Interpretation and use of test results are the responsibility of the client. This report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST or any agency of the federal government. Non-friable organically bound materials present a problem matrix and therefore EMSL recommends gravimetric reduction prior to analysis. Samples received in good condition unless otherwise noted. Estimated accuracy, precision and uncertainty data available upon request. Unless requested by the client, building materials manufactured with multiple layers (i.e. linoleum, wallboard, etc.) are reported as a single sample. Reporting limit is 1%

Samples analyzed by EMSL Analytical, Inc San Leandro, CA NVLAP Lab Code 101048-3, WA C884

Initial report from 05/01/2015 12:44:26