

Specification 2.1.A.1

Interior Wet Coating System
(Below the Overflow Level)

International

PRODUCT DESCRIPTION

A low VOC, two component high build, high solids surface tolerant epoxy maintenance coating.

INTENDED USES

For application to a wide variety of substrates including hand prepared rusty steel, abrasive blast cleaned and hydroblasted steel, and a wide range of intact, aged coatings. Provides excellent anti-corrosive protection in industrial, coastal structures, pulp and paper plants, bridges and offshore environments in both atmospheric exposure and immersion service.

NSF Certification is for tanks greater than 100 gallons (378.5 litres).



Certified to NSF/ANSI 61

PRACTICAL INFORMATION FOR INTERSEAL 670HS

Colour	Available in a wide range of colours including Aluminium
Gloss Level	Semi-gloss (Aluminium is eggshell)
Volume Solids	82% ± 3% (depends on colour)
Typical Thickness	100-250 microns (4-10 mils) dry equivalent to 122-305 microns (4.9-12.2 mils) wet
Theoretical Coverage	6.56 m ² /litre at 125 microns d.f.t and stated volume solids 263 sq.ft/US gallon at 5 mils d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless spray, Air spray, Brush, Roller

Drying Time ▲

Temperature	Touch Dry	Hard Dry	Overcoating Interval Interseal 670HS with Self			Overcoating Interval with recommended topcoats		
			Min	Max ●	Max †	Min	Max ●	Max †#
10°C (50°F)	8 hours	32 hours	32 hours	6 weeks	Extended*	20 hours	21 days	12 weeks
15°C (59°F)	7 hours	26 hours	26 hours	4 weeks	Extended*	14 hours	14 days	8 weeks
25°C (77°F)	5 hours	18 hours	18 hours	14 days	Extended*	10 hours	7 days	4 weeks
40°C (104°F)	2 hours	6 hours	6 hours	7 days	Extended*	4 hours	3 days	2 weeks

▲ For curing at low temperatures, an alternative curing agent is available. See Product Characteristics for details.

● Refers to situations where immersion is likely to occur

† Refer to atmospheric service only

* See International Protective Coatings Definitions & Abbreviations

Maximum overcoating intervals are shorter when using polysiloxane topcoats. Consult International Protective Coatings for further details.

REGULATORY DATA

Flash Point (Typical)	Base (Part A) 36°C (97°F) Curing Agent (Part B) 56°C (133°F)	Mixed 33°C (91°F)
Product Weight	1.6 kg/l (13.3 lb/gal)	
VOC	114 g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)
	2.00 lb/gal (240 g/l)	EPA Method 24
	151 g/l	Chinese National Standard GB23985

Surface Tolerant Epoxy

SURFACE PREPARATION

The performance of this product will depend upon the degree of surface preparation. The surface to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

Abrasive Blast Cleaning

For immersion service, Interseal 670HS must be applied to surfaces blast cleaned to Sa2.5 (ISO 8501-1:2007) or SSPC-SP10. However, for atmospheric exposure best performance will be achieved when Interseal 670HS is applied to surfaces prepared to a minimum of Sa2.5 (ISO 8501-1:2007) or SSPC-SP6.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

A surface profile of 50-75 microns (2-3 mils) is recommended.

Hand or Power Tool Preparation

Hand or power tool clean to a minimum St2 (ISO 8501-1:2007) or SSPC-SP2.

Note, all scale must be removed and areas which cannot be prepared adequately by chipping or needle gun should be spot blasted to a minimum standard of Sa2 (ISO 8501-1:2007) or SSPC-SP6. Typically this would apply to C or D grade rusting in this standard.

Ultra High Pressure Hydroblasting/Abrasive Wet Blasting

May be applied to surfaces prepared to Sa2.5 (ISO 8501-1:2007) or SSPC-SP6 which have flash rusted to no worse than Grade HB2.5M (refer to International Hydroblasting Standards) or Grade SB2.5M (refer to International Slurry blasting Standards). It is also possible to apply to damp surfaces in some circumstances. Further information is available from International Protective Coatings.

Aged Coatings

Interseal 670HS is suitable for overcoating a limited range of intact, tightly adherent aged coatings. Loose or flaking coatings should be removed back to a firm edge. Glossy finishes may require light abrasion to provide a physical 'key'. See Product Characteristics section for further information.

APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
Mix Ratio	5.67 parts : 1.00 part by volume			
Working Pot Life	10°C (50°F)	15°C (59°F)	25°C (77°F)	40°C (104°F)
	5 hours	3 hours	2 hours	1 hour
Airless Spray	Recommended	Tip range 0.45-0.58 mm (18-23 thou) Total output fluid pressure at spray tip not less than 176 kg/cm² (2,500 p.s.i.)		
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
Brush	Recommended	Typically 100-125 microns (4-5 mils) can be achieved		
Roller	Recommended	Typically 75-100 microns (3-4 mils) can be achieved		
Thinner	International GTA220 (or GTA415)	Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.		
Cleaner	International GTA822 (or GTA415)			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Surface Tolerant Epoxy

PRODUCT CHARACTERISTICS

For water immersion service, surface preparation to a minimum of Sa2.5 (ISO 8501-1:2007) or SSPC-SP10 followed by application of multi-coats of Interseal 670HS to a total minimum dry film thickness of 250 microns (10 mils) is required.

Colours derived from chromascan bases as the first coat of a specification for immersion service is not recommended.

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved. Application by air spray may require a multiple cross spray pattern to attain maximum film build. Low or high temperatures may require specific application techniques to achieve maximum film build.

If salt water is used in the wet blast process the resulting surface must be thoroughly washed with fresh water before application of Interseal 670HS. With freshly blasted surfaces a slight degree of flash rusting is allowable, and is preferable to the surface being too wet. Puddles, ponding and accumulations of water must be removed.

Interseal 670HS may be applied to suitably sealed or primed concrete; contact International Protective Coatings for further advice on specification and primers.

Interseal 670HS is suitable for overcoating intact, aged alkyd, epoxy and polyurethane systems. However, this product is not recommended where thermoplastic coatings such as chlorinated rubbers and vinyls have previously been used. Please consult International Protective Coatings for alternative recommendations.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Level of sheen and surface finish is dependent on application method. Avoid using a mixture of application methods whenever possible.

In common with all epoxies Interseal 670HS will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

Premature exposure to ponding water will cause a colour change, especially in dark colours.

Interseal 670HS can be used as a non-skid deck system by modification with addition of GMA132 (crushed flint) aggregate. Application should then be to a suitably primed surface. Typical thicknesses will be between 500-1,000 microns (20-40 mils). Preferred application is by a suitable large tip hopper gun (e.g. Sagola 429 or Air texture gun fitted with a 5-10 mm nozzle). Trowel or roller can be used for small areas. Alternatively, a broadcast method of application can be used. Consult International Protective Coatings for further details.

Interseal 670HS is certified to NSF/ANSI Standard 61 (selected colours only). Consult International Protective Coatings for further details. Certification is for tanks greater than 100 gallons (378.5 litres), for pipes which are 6 inches (15 cm) in diameter or greater and for valves which are 2 inches (5 cm) in diameter or greater.

Low Temperature Curing

A winter grade curing agent is also available to enable more rapid cure at temperatures less than 10°C (50°F), however this curing agent will give an initial shade variation and more rapid discoloration on weathering.

Interseal 670HS is capable of curing at temperatures below 0°C (32°F). However, this product should not be applied at temperatures below 0°C (32°F) where there is a possibility of ice formation on the substrate.

Temperature	Touch Dry	Hard Dry	Overcoating Interval Interseal 670HS with Self			Overcoating Interval with recommended topcoats		
			Min	Max •	Max †	Min	Max •	Max †
-5°C (23°F)	24 hours	72 hours	72 hours	12 weeks	Extended*	72 hours	84 hours	12 weeks
0°C (32°F)	16 hours	56 hours	56 hours	10 weeks	Extended*	42 hours	54 hours	10 weeks
5°C (41°F)	9 hours	36 hours	36 hours	8 weeks	Extended*	36 hours	48 hours	8 weeks
10°C (50°F)	5 hours	24 hours	24 hours	6 weeks	Extended*	16 hours	24 hours	6 weeks

• Refers to situations where immersion is likely to occur

† Refer to atmospheric service only

* See International Protective Coatings Definitions & Abbreviations

Touch dry times shown above are actual drying times due to chemical cure, rather than physical set due to solidification of the coating film at temperatures below 0°C (32°F).

Note: VOC values quoted are based on maximum possible for the product taking into account variations due to colour differences and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24

SYSTEMS COMPATIBILITY

Interseal 670HS will normally be applied to correctly prepared steel substrates. However, it can be used over suitably primed surfaces. Suitable primers are:

- Intercure 200
- Interzinc 315
- Interplus 356
- Interplus 256
- Intergard 269

Where a cosmetically acceptable topcoat is required the following products are recommended:

- Intercryl 530
- Interfine 878
- Intergard 740
- Interthane 990
- Interfine 629HS
- Interfine 979
- Interthane 870

Other suitable primers/topcoats are available. Consult International Protective Coatings.

Surface Tolerant Epoxy

ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size		Part A		Part B	
		Vol	Pack	Vol	Pack	
	20 litre	17 litre	20 litre	3 litre	3.7 litre	
	5 US gal	4.25 US Gal	5 US Gal	0.75 US Gal	1 US gal	
For availability of other pack sizes, contact International Protective Coatings						

SHIPPING WEIGHT (TYPICAL)	Unit Size		Part A		Part B	
	20 litre		30.8 kg		3.5 kg	
	5 US gal		64.9 lb		6.8 lb	

STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. Protect from frost.
---------	------------	--

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 28/10/2015.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

www.international-pc.com

PRODUCT DESCRIPTION

A two component solvent free elastomeric urethane.

Polibrid 705E is fast setting and can be applied by heated, plural component airless spray to offer the ultimate protection in corrosive environments. Geotextile fabrics may be embedded within the coating to produce reinforced, bonded geomembrane linings.

Polibrid 705E repair kits are also available for hand patching relatively small areas of previously applied Polibrid 705E.

INTENDED USES

Polibrid 705E is an ultra high-build, flexible coating designed to protect concrete and steel in chemical, abrasion and high impact environments, ideal for encapsulation of rivets, bolts, edges and other surface imperfections.

The product is odourless with zero VOC thus eliminating the creation of pinholes due to solvent evaporation producing a dense, elastic membrane capable of withstanding shrinkage cracks in concrete.

Polibrid 705E can be applied as a lining for various chemicals, potable water and wastewater services or for secondary containment. These characteristics and ability to provide rapid return to service make it ideal for the Water & Waste Water, Mining & Minerals markets and a range of other industrial applications.

PRACTICAL INFORMATION FOR POLIBRID 705E

Colour	Buff
Gloss Level	Not applicable
Volume Solids	100%
Typical Thickness	700-5000 microns (28-200 mils) dry equivalent to 700-5000 microns (28-200 mils) wet
Theoretical Coverage	0.50 m ² /litre at 2000 microns d.f.t and stated volume solids 20 sq.ft/US gallon at 80 mils d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Plural Component Airless Spray

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating interval with self	
			Minimum	Maximum
15°C (59°F)	2 hours	2 days	*	2 hours ¹
25°C (77°F)	1 hour	1 day	*	1 hour ¹
40°C (104°F)	40 minutes	1 day	*	40 minutes ¹

¹ The values quoted are those achieved when exposed to direct sunlight. In shaded or cloudy conditions, maximum recoat values are increased as follows ; 15°C (59°F) – 6 hours ; 25°C (77°F) – 4 hours ; 40°C (104°F) – 1 hour

REGULATORY DATA

Flash Point (Typical)	Part A 260°C (500°F); Part B 110°C (230°F); Mixed 110°C (230°F)		
Product Weight	1.14 kg/l (9.5 lb/gal)		
VOC	0.00 lb/gal (0 g/l)	EPA Method 24	

See Product Characteristics section for further details

**SURFACE
PREPARATION**

Please consult the Polibrid 705E Application Guidelines prior to commencing surface preparation.

Steel

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all steel surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 Solvent Cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP10. If oxidation has occurred between blasting and application of Polibrid 705E, the surface should be reblasted to the specified visual standard. Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

A sharp, angular profile of 90 microns (3.6 mils) is recommended as a minimum.

The preferred method of holding the blast standard is by dehumidification. Alternatively, an approved holding primer may be used.

Concrete

For applications over concrete substrates, the use of a geotextile fabric should always be considered. Please consult the Polibrid 705E Application Guidelines for further details of surface preparation and application.

APPLICATION

Mixing	This material is supplied in full containers for use with plural component airless spray equipment. Once mixed, Polibrid 705E must be used within the working pot life specified.		
	Thoroughly mix Part A with air-driven agitator for 30 minutes just prior to use. Part B requires no agitation before using.		
Mix Ratio	2 part(s) : 1 part(s) by volume		
Working Pot Life	15°C (59°F) 5 minutes	25°C (77°F) 3 minutes	40°C (104°F) 1 minute
Airless Spray	Recommended	Tip Range 0.63-0.89 mm (25-35 thou) Total output fluid pressure at spray tip not less than 211 kg/cm² (3000 p.s.i.)	
Air Spray (Pressure Pot)	Not recommended		
Brush	Suitable	Small areas and stripe coating only	
Roller	Not recommended		
Thinner	Not suitable	DO NOT THIN	
Cleaner	International GTA203 -	N.B Clean all equipment immediately after use.	
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA203.		
Clean Up	Clean all equipment immediately after use with International GTA203. It is good working practice to periodically flush out spray equipment during the course of the working day. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		
	Note: After flushing equipment with GTA203 cleaner during clean up and work stoppages, it is recommended that a final purge is carried out with GTA004 to remove any moisture prior to storing the equipment.		

**PRODUCT
CHARACTERISTICS**

The detailed Polibrid 705E Application Guidelines should be consulted prior to use.

Only companies in receipt of Qualified Applicator status from International Protective Coatings shall be used for Polibrid 705E application. Companies shall document that they comply with this requirement prior to work commencement.

This datasheet provides general guidance on the use of Polibrid 705E. Specific project requirements will be dependent upon the service end use and operating conditions of the tank or vessel.

The detailed project coating specification provided by International Protective Coatings must be followed at all times.

When applying to concrete substrates, application of Polibrid 705E should always be carried out during the cooling periods of the day.

This product will not cure adequately below -4°C (25°F) or at relative humidity above 95%. For maximum performance, ambient curing temperatures should be between 4°C and 49°C (40-120°F).

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Polibrid 705E is sensitive to the presence of moisture and must not be applied to wet or damp substrates at any time.

Maximum continuous dry temperature resistance for Polibrid 705E is 82°C (180°F).

Maximum continuous immersed temperature resistance for Polibrid 705E is 49°C (120°F) for insulated tanks and vessels.

A minimum Shore D hardness reading of 60 is a recommended guideline to indicate suitability for return to service.

This product is not recommended for exposure to concentrated acids, aromatic hydrocarbons, ketones or chlorinated solvents.

Due to its aromatic composition, Polibrid 705E will tend to yellow or darken in colour after exposure to UV light.

This product has the following specification approvals:
Certified to AS/NZS 4020:2005 for tanks less than 1000 mm²/litre.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

**SYSTEMS
COMPATIBILITY**

Polibrid 705E should always be applied to correctly prepared substrates. When a primer is required as part of the coating specification, consult International Protective Coatings for specific advice.

**ADDITIONAL
INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Polibrid 705E Application Guidelines

Individual copies of these information sections are available upon request.

**SAFETY
PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

Warning: Contains isocyanate. Wear air-fed hood for spray application.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	203 litre	200 litre	200 litre	200 litre	200 litre
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT (TYPICAL)					
* Consult International Protective Coatings for advice					
STORAGE	Shelf Life	24 months (Part A) & 12 months (Part B) minimum at 25°C (77°F) Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			
		For maximum shelf life, it is recommended that Part B is stored at temperatures between 25°C (77°F) and 40°C (104°F). Absolute minimum storage temperature is 15°C (59°F).			

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Copyright © AkzoNobel, 04/07/2012.

 International, International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

www.international-pc.com

Specification 2.1.A.1

Interior Wet Coating System
(Below the Overflow Level)

Tnemec



PRODUCT PROFILE

GENERIC DESCRIPTION	Aromatic Urethane, Zinc-Rich
COMMON USAGE	A single-component, moisture-cured, zinc-rich primer for steel structures, including the interior and exterior of steel potable water tanks. Provides outstanding long-term corrosion resistance when used as a primer in conjunction with other Tnemec coatings. It cures quickly and offers rapid recoat at surface temperatures down to 35°F. Note: When used in conjunction with cathodic protection, anodes or impressed current systems should not provide current demand more negative than -1.05 volts relative to a copper-copper sulfate reference electrode half-cell.
COLORS	Greenish-gray
ZINC PIGMENT	83% by weight in dried film
SPECIAL QUALIFICATIONS	Certified (with or without 44-710 Urethane Accelerator) in accordance with ANSI/NSF Std. 61 for use on interior potable water tanks of 400 gallons or greater. Topcoating with Std. 61 certified Tnemec coatings is recommended. Contact your Tnemec representative for specific recommendations. Meets zinc-rich primer requirements of AWWA D102-11 Standard for Inside System No. 3 & 5 and Outside System No. 3, 4 & 6 . Series 94-H ₂ O uses a zinc pigment which meets the requirements of ASTM D 520 Type III and contains less than .002% lead. Reference "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT.
PERFORMANCE CRITERIA	Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

TOPCOATS	Interior: Series 20, FC20, 22, FC22, L140, L140F, N140, N140F, V140, V140F, 141, 215, 406 Exterior: Series 27WB, 66, L69, L69F, N69, N69F, V69, V69F, 73, 115, 156, 161, 215, 1028, 1029, 1074, 1074U, 1075, 1075U, 1080, 1081. Note: Certain topcoat colors may not provide one-coat hiding depending on method of application. Contact your Tnemec representative. Note: Series 94-H ₂ O must be exterior exposed for three days prior to topcoating with Series 1028 or 1029. Note: Series 94-H ₂ O must be exterior exposed for one day prior to topcoating with Series 27WB.
-----------------	---

SURFACE PREPARATION

Wet Interior: SSPC-SP10/NACE 2 Near-White Blast Cleaning with a minimum angular anchor profile of 2.0 mils.
Exterior or Dry Interior: SSPC-SP6/NACE 3 Commercial Blast Cleaning with a minimum angular anchor profile of 2.0 mils.

TECHNICAL DATA

VOLUME SOLIDS	62.0 ± 2.0% (mixed)
RECOMMENDED DFT	2.5 to 3.5 mils (65 to 90 microns) per coat.
CURING TIME	Without 44-710

Temperature †	To Handle	To Recoat
75°F (24°C)	2 hours	8 hours
55°F (11°C)	4 hours	12 hours
35°F (2°C)	6 hours	16 hours

† 50% relative humidity. **Note:** Refer to product listings on www.nsf.org for specific potable water return to service information. Curing time will vary with surface temperature, humidity and film thickness. **Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure.
Note: For faster curing, low humidity and low-temperature applications, add No. 44-710 Urethane Accelerator (see separate product data sheet). **Note:** For cure times to immersion service, reference the specified Tnemec interior topcoat product data sheet.

VOLATILE ORGANIC COMPOUNDS	Unthinned: 0.74 lbs/gallon (89 grams/litre) Thinned 15% (No. 49 Thinner): 0.74 lbs/gallon (89 grams/litre) Thinned 10% (No. 3 Thinner): 1.57 lbs/gallon (188 grams/litre) Thinned 10% (No. 2 Thinner): 1.56 lbs/gallon (187 grams/litre)
HAPS	Unthinned: 2.11 lbs/gal solids Thinned 15% (No. 49 Thinner): 2.11 lbs/gal solids Thinned 10% (No. 3 Thinner): 2.15 lbs/gal solids Thinned 10% (No. 2 Thinner): 3.28 lbs/gal solids
THEORETICAL COVERAGE	996 mil sq ft/gal (24.4 m ² /L at 25 microns). See APPLICATION for coverage rates.
NUMBER OF COMPONENTS	One
PACKAGING	5 gallon (18.9L) pails (yielding 3 gallons) and 1 gallon (3.79L) cans.
NET WEIGHT PER GALLON	24.92 ± 0.60 lbs (11.30 ± .27 kg)
STORAGE TEMPERATURE	Minimum 20°F (-7°C) Maximum 110°F (43°C)
TEMPERATURE RESISTANCE	Dry (Continuous) 250°F (121°C) Intermittent 300°F (149°C)
SHELF LIFE	9 months at recommended storage temperature.
FLASH POINT - SETA	82°F (28°C)
HEALTH & SAFETY	Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. Keep out of the reach of children.

HYDRO-ZINC® | SERIES 94-H₂O

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Suggested	3.0 (75)	5.0 (125)	331 (30.8)
Minimum	2.5 (65)	4.0 (100)	398 (37.0)
Maximum	3.5 (90)	5.5 (140)	284 (26.4)

Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT.

MIXING

Stir thoroughly making sure no pigment remains on the bottom of the can. Use an air-driven power mixer and keep material under constant agitation while mixing. Do not use material beyond pot life limits.

THINNING

For air spray, thin up to 15% or 1 1/4 pints (570 mL) per gallon with No. 49 Thinner or thin up to 10% or 3/4 pint (380 mL) per gallon with No. 2 or No. 3 Thinner. For brush or roller, thin up to 5% or 1/4 pint (190 mL) per gallon with No. 49 Thinner or thin up to 10% or 3/4 pint (380 mL) per gallon with No. 2 or No. 3 Thinner. Thinning is normally not required for airless spray. **Note:** No. 49 Thinner may be used where VOC restrictions apply. **Caution: Series 94-H₂O certification is based on thinning with No. 49, No. 2 or No. 3 Thinner. Use of any other thinner voids NSF/ANSI Std. 61 certification.**

POT LIFE

8 hours at 77°F (25°C) and 50% R.H.

Caution: This product cures with moisture acting as a catalyst. Incorporation of moisture or moisture laden air (humidity) during use will shorten pot life. Avoid continual agitation at high RPM. When feasible keep containers of mixed material covered during use.

APPLICATION EQUIPMENT

Note: When intermediate and finish coats are white or light colors, best hiding of this dark color primer can be achieved by spray application; or when roller applied, by using 1/4" nap covers.

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA †	E	704 or 765	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	40-50 psi (2.8-3.4 bar)	10-20 psi (0.7-1.4 bar)

† (with heavy mastic spring) Low temperatures or longer hoses will require additional pressure. Use pressure pot equipped with an agitator and keep pressure pot at same level or higher than the spray gun. Compressed air must be dry.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-481 microns) Reversible Tip	3000-4000 psi (207-276 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use a 1/4" or 3/8" (6.4 mm or 9.5 mm) synthetic woven nap roller cover. Stir material frequently or keep under agitation to prevent settling.

Brush: Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 35°F (2°C) Maximum 140°F (60°C) Maximum for Brush & Roller 120°F (49°C)

The surface should be dry and at least 5°F (3°C) above the dew point. **Note:** Series 44-710 Accelerator must be used if the surface temperature is 35°F to 60°F (2°C to 16°C) and 20% to 40% relative humidity. Please reference Technical Bulletin 98-14 for more information.

AMBIENT HUMIDITY

Minimum 20% Maximum 90%

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or xylene or, when required by SCAQMD regulations, No. 49 Thinner.

CAUTION

Series 94-H₂O, with one-component configuration, prevents the product's ability to offer "dry-fall" characteristics.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

POTA-POX® PLUS SERIES N140F

PRODUCT PROFILE

GENERIC DESCRIPTION	Polyamidoamine Epoxy
COMMON USAGE	Innovative potable water coating which offers high-build edge protection and allows for application at a wide range of temperatures (down to 35°F or 2°C). For use on the interior and exterior of steel or concrete tanks, reservoirs, pipes, valves, pumps and equipment in potable water service.
COLORS	1211 Red, 1255 Beige, 00WH Tnemec White, 15BL Tank White, 39BL Delft Blue, 35GR Black. Note: Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.
SPECIAL QUALIFICATIONS	Certified by NSF International in accordance with NSF/ANSI Std. 61 . Ambient air cured Series N140F is qualified for use on tanks and reservoirs of 1,000 gallons (3,785 L) capacity or greater, pipes 18 inches (46 cm) in diameter or greater and valves four (4) inches (10 cm) in diameter or greater. Series N140F is certified by NSF International in accordance with NSF/ANSI Std. 50 for pools and other recreational water facilities. Conforms to AWWA D 102 Inside Systems No. 1 and No. 2 . Contact your Tnemec representative for systems and additional information. A two-coat system at 4.0-6.0 dry mils (100-150 dry microns) per coat passes the performance requirements of MIL-PRF-4556F for fuel storage. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT.
PERFORMANCE CRITERIA	Extensive test data available. Contact your Tnemec representative for specific test results.

COATING SYSTEM

SURFACER/FILLER/PATCHER	215, 217, 218
PRIMERS	Self-priming, 22, 91-H ₂ O, 94-H ₂ O, L140, L140F, N140, V140, 141
TOPCOATS	Interior: Series 22, FC22, L140, L140F, N140, N140F, V140, V140F, 141, 406 Exterior: Series 27, 66, L69, L69F, N69, N69F, V69, V69F, 72, 73, L140, L140F, N140, N140F, V140, V140F, 156, 157, 161, 175, 180, 181, 446, 740, 750, 1028, 1029, 1074, 1074U, 1075, 1075U, 1077, 1078, 1080, 1081. Refer to COLORS on applicable topcoat data sheets for additional information. Note: The following recoat times apply for Series N140F: Immersion Service—Surface must be scarified by blasting with fine abrasive after 30 days. Atmospheric Service—After 30 days, scarification or an epoxy tie-coat is required. When topcoating with Series 740 or 750, recoat time for N140F is 14 days. Contact your Tnemec representative for specific recommendations.

SURFACE PREPARATION

PRIMED STEEL	Immersion Service: Scarify the epoxy prime coat surface by abrasive blasting with fine abrasive before topcoating if it has been exterior exposed for 30 days or longer and N140F is the specified topcoat.
STEEL	Immersion Service: SSPC-SP10/NACE 2 Near-White Blast Cleaning with a minimum angular anchor profile of 1.5 mils Non-Immersion Service: SSPC-SP6/NACE 3 Commercial Blast Cleaning with a minimum angular anchor profile of 1.5 mils.
CAST/DUCTILE IRON	Contact your Tnemec Representative or Tnemec Technical Services.
CONCRETE	Allow new concrete to cure 28 days. For optimum results and/or immersion service, abrasive blast referencing SSPC-SP13/NACE 6, ICRI-CSP 2-4 Surface Preparation of Concrete and Tnemec's Surface Preparation and Application Guide. Fill all holes, pits, voids and cracks with 215 or 218.
ALL SURFACES	Must be clean, dry and free of oil, grease and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS	68.0 ± 2.0% (mixed) †
RECOMMENDED DFT	2.0 to 10.0 mils (50 to 225 microns) per coat. Note: MIL-PRF-4556F applications require two coats at 4.0-6.0 mils (100-150 microns) per coat. Otherwise, the number of coats and thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME AT 5 MILS DFT	Temperature	To Handle	To Recoat	Immersion
	75°F (24°C)	4 hours	5 hours	7 days
	65°F (18°C)	7-8 hours	9-11 hours	8 days
	55°F (13°C)	12-14 hours	16-20 hours	9-10 days
	45°F (7°C)	18-22 hours	28-32 hours	12-13 days
	35°F (2°C)	28-32 hours	46-50 hours	16-18 days

Curing time varies with surface temperature, air movement, humidity and film thickness.

Note: For valve applications allow 14 days cure at 75°F (24°C) prior to immersion. For pipe applications allow 30 days cure at 75°F (24°C) prior to immersion. **Ventilation:** When used in enclosed areas, provide adequate ventilation during application and cure. **Note:** Refer to product listings on www.nsf.org for specific potable water return to service information.

VOLATILE ORGANIC COMPOUNDS	Unthinned: 2.3 lbs/gallon (273 grams/litre) Thinned 5% (#60): 2.5 lbs/gallon (299 grams/litre) Thinned 10% (#4): 2.7 lbs/gallon (323 grams/litre) †
-----------------------------------	--

HAPS	Unthinned: 2.3 lbs/gal solids Thinned 5% (#60): 2.3 lbs/gal solids Thinned 10% (#4): 3.1 lbs/gal solids
-------------	--

THEORETICAL COVERAGE 1,094 mil sq ft/gal (26.8 m²/L at 25 microns). See APPLICATION for coverage rates. †

NUMBER OF COMPONENTS Two: Part A (amine) and Part B (epoxy) — One (Part A) to one (Part B) by volume.

PACKAGING 5 gallon (18.9L) pails and 1 gallon (3.79L) cans — Order in multiples of 2.

POTA-POX® PLUS | SERIES N140F

NET WEIGHT PER GALLON	12.68 ± 0.25 lbs (5.75 ± .11 kg) (mixed) †
STORAGE TEMPERATURE	Minimum 20°F (-7°C) Maximum 110°F (43°C) For optimum application properties, material temperature should be above 60°F (16°C) prior to application.
TEMPERATURE RESISTANCE	(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)
SHelf LIFE	Part A: 24 months; Part B: 12 months at recommended storage temperature.
FLASH POINT - SETA	Part A: 82°F (28°C) Part B: 80°F (27°C)
HEALTH & SAFETY	Paint products contain chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product. Keep out of the reach of children.

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m²/Gal)
Suggested	6.0 (150)	9.0 (230)	182 (16.9)
Minimum	2.0 (50)	3.0 (75)	545 (50.7)
Maximum	10.0 (225)	15.0 (375)	109 (10.1)

Note: Roller or brush application requires two or more coats to obtain recommended film thickness. Allow for overspray and surface irregularities. Wet film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT. †

MIXING

1. Start with equal amounts of both Parts A & B.
2. Using a power mixer, separately stir Parts A & B.
3. Add Part A to Part B under agitation, stir until thoroughly mixed.
4. Both components should be above 50°F (10°C) prior to mixing. For application to surfaces between 35°F to 50°F (2°C to 10°C), allow mixed material to stand thirty (30) minutes and restir before using. For optimum application properties, blended components should be above 40°F (4°C).

THINNING

N140F: Use No. 4 or No. 60 Thinner. For air spray, thin up to 10% or 3/4 pint (380 mL) per gallon with No. 4 Thinner or thin up to 5% or 1/4 pint (190 mL) per gallon with No. 60 Thinner. For airless spray, roller or brush, thin up to 5% or 1/4 pint (190 mL) per gallon. **Caution: Series N140F NSF certification is based on thinning with No. 4 or No. 60 Thinner for tanks and only No. 60 Thinner for pipe and valves.** Use of any other thinner voids NSF/ANSI Std. 61 certification. V140F: Use No. 4 Thinner. **Caution: Series V140F NSF certification is based on thinning with No. 4 Thinner only.** Use of any other thinner voids NSF/ANSI Std. 61 certification. **Note:** When using Series V140F, a maximum of 4.5% of No. 4 Thinner may be used to comply with VOC regulations.

POT LIFE

2 hours at 50°F (10°C) 1 hour at 75°F (24°C) 30 minutes at 100°F (38°C)

SPRAY LIFE

30 minutes at 75°F (24°C)

Note: Spray application after listed times will adversely affect ability to achieve recommended dry film thickness.

APPLICATION EQUIPMENT

Air Spray

Gun	Fluid Tip	Air Cap	Air Hose ID	Mat'l Hose ID	Atomizing Pressure	Pot Pressure
DeVilbiss JGA	E	765 or 704	5/16" or 3/8" (7.9 or 9.5 mm)	3/8" or 1/2" (9.5 or 12.7 mm)	75-100 psi (5.2-6.9 bar)	10-20 psi (0.7-1.4 bar)

Low temperatures or longer hoses require higher pot pressure.

Airless Spray

Tip Orifice	Atomizing Pressure	Mat'l Hose ID	Manifold Filter
0.015"-0.019" (380-485 microns)	3000-4800 psi (207-330 bar)	1/4" or 3/8" (6.4 or 9.5 mm)	60 mesh (250 microns)

Use appropriate tip/atomizing pressure for equipment, applicator technique and weather conditions.

Roller: Use 3/8" or 1/2" (9.5 mm to 12.7 mm) synthetic woven nap roller cover. Use longer nap to obtain penetration on rough or porous surfaces.

Brush: Recommended for small areas only. Use high quality natural or synthetic bristle brushes.

SURFACE TEMPERATURE

Minimum 35°F (2°C) Maximum 135°F (57°C)

The surface should be dry and at least 5°F (3°C) above the dew point. Coating won't cure below minimum surface temperature.

CLEANUP

Flush and clean all equipment immediately after use with the recommended thinner or MEK.

† Values may vary with color.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company Incorporated 6800 Corporate Drive Kansas City, Missouri 64120-1372 1-800-TNEMEC1 Fax: 1-816-483-3969 www.tnemec.com

PRODUCT PROFILE

GENERIC DESCRIPTION

Modified Polyamine Epoxy

COMMON USAGE

An advanced generation, 100% solids epoxy liner for the protection of steel and concrete. It provides excellent resistance to abrasion and is suitable for immersion and chemical contact. For use on the interior and exterior of steel or concrete tanks, reservoirs, and pipes in potable water service.

COLORS

WH08 White. **Note:** Epoxies chalk with extended exposure to sunlight. Lack of ventilation, incomplete mixing, miscatalyzation or the use of heaters that emit carbon dioxide and carbon monoxide during application and initial stages of curing may cause yellowing to occur.

FINISH

Semi-Gloss

SPECIAL QUALIFICATIONS

Certified by **NSF International** in accordance with **NSF/ANSI Std. 61**. Ambient air cured Series FC22 is qualified for use on tanks and reservoirs of 5 gallons (18.9 L) capacity or greater and pipes and valves 1/2 inch (1.2 cm) in diameter or greater. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT. Conforms to **AWWA D 102 Inside System No. 3**. Conforms to **AWWA C 210**. Contact your Tnemec representative for systems and additional information.

COATING SYSTEM

SURFACER/FILLER/PATCHER

Series 215, 218

PRIMERS

Self-priming or Series 1, 91-H₂O, 94-H₂O, L140, L140F, N140, N140F, V140, V140F

SURFACE PREPARATION

STEEL

Non-Immersion Service: SSPC-SP6/NACE 3 Commercial Blast Cleaning with a minimum angular anchor profile of 3.0 mils for dry film thicknesses at 16.0 to 20.0 mils.

Immersion Service: SPC-SP10/NACE 2 Near-White Blast Cleaning with a minimum angular anchor profile of 3.0 mils for dry film thicknesses at 20.0 mils or greater.

Note: When self-priming on steel, a minimum angular anchor profile of 3.0 mils is required. For all other applications, refer to the primer data sheet for recommendations.

CONCRETE

Allow new concrete to cure 28 days. Verify dryness by testing for moisture with a "plastic film tape-down test" (Reference ASTM D 4263). If necessary for testing horizontal surfaces, perform "Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride" (Reference ASTM F 1869). Moisture content not to exceed three pounds per 1,000 sq ft in a 24 hour period. Abrasive blast or mechanically abrade to remove laitance, form release agents, curing compounds, sealers and other contaminants and to provide surface profile (Reference SSPC-SP13, ICRI CSP-5). Voids, bugholes and other cavities should be filled with recommended filler or surfacer.

ALL SURFACES

Must be clean, dry and free of oil, grease, chalk and other contaminants.

TECHNICAL DATA

VOLUME SOLIDS

100% (mixed)

RECOMMENDED DFT

16.0 to 40.0 mils (405 to 1015 microns) in a one coat application. **Note:** Thickness requirements will vary with substrate, application method and exposure. Contact your Tnemec representative.

CURING TIME

Temperature	To Handle	Max to Recoat	Immersion
110°F (43°C)	1 hour	7 days	16 hours
75°F (24°C)	6 hours	7 days	24 hours
35°F (2°C)	12 hours	7 days	48 hours

Note: These times are based on a 20.0 mil (500 micron) dry film thickness. Curing time varies with surface temperature, air movement, humidity and film thickness. **Ventilation:** When used as a tank lining or in enclosed areas, provide adequate ventilation during application and cure.

VOLATILE ORGANIC COMPOUNDS

EPA Method 24 **Unthinned:** 0.04 lbs/gallon (5 grams/litre)

THEORETICAL COVERAGE

1,604 mil sq ft/gal (39.4 m²/L at 25 microns.) See APPLICATION for coverage rates.

NUMBER OF COMPONENTS

Two: 1 (Part A amine) to 2 (Part B epoxy)

PACKAGING

	PART A	PART B	When Mixed
Large Kit	1-5 gallon pail	2-6 gallon pails	15 gallons (56.78 L)
Touch-Up Kit (1 tube)	2 ounces	4 ounces	6 ounces (175 mL)

Note: Touch-Up Kit consists of six (6) tubes along with twelve (12) disposable static mixers.

NET WEIGHT PER GALLON

13.36 ± 0.25 lbs (6.06 ± .11 kg) (mixed)

STORAGE TEMPERATURE

Minimum 20°F (-6°C) Maximum 110°F (43°C)
For optimal handling and application characteristics, both material components should be stored at a minimum of 70°F (21°C) or higher for 48 hours prior to use.

TEMPERATURE RESISTANCE

(Dry) Continuous 250°F (121°C) Intermittent 275°F (135°C)

SHELF LIFE

12 months at recommended storage temperature.

FLASH POINT - SETA

Part A and Part B: N/A

HEALTH & SAFETY

This product contains chemical ingredients which are considered hazardous. Read container label warning and Material Safety Data Sheet for important health and safety information prior to the use of this product.
Keep out of the reach of children.

EPOXOLINE® | SERIES FC22

APPLICATION

COVERAGE RATES

	Dry Mils (Microns)	Wet Mils (Microns)	Sq Ft/Gal (m ² /Gal)
Minimum	16.0 (405)	16.0 (405)	100 (9.3)
Maximum	40.0 (1015)	40.0 (1015)	40 (3.7)

Allow for overspray and surface irregularities. Film thickness is rounded to the nearest 0.5 mil or 5 microns. Application of coating below minimum or above maximum recommended dry film thicknesses may adversely affect coating performance. Reference the "Search Listings" section of the NSF website at www.nsf.org for details on the maximum allowable DFT.

MIXING

Large Kit: Agitate Parts A & B making sure no pigment remains on the bottom of the can. **DO NOT MIX PART A WITH PART B.** Use a 1 (Part A amine) to 2 (Part B epoxy) mix ratio heated plural component airless spray unit. **Note:** Product component A (amine) must be heated to 110°F to 120°F (43°C to 49°C) and component B (epoxy) must be heated to 120°F to 130°F (49°C to 54°C) prior to and during plural component application. Do not heat component A (amine) above 120°F (49°C) or component B (epoxy) above 130°F (54°C). Prior to use: Keep containers tightly sealed.

Touch-Up Kit: Equipment: A dispensing gun with a thrust ratio of 26:1 is required (F100-TKAP). Material tube must be used in conjunction with provided disposable static mixer in order to ensure proper mixing.

Usage: Unscrew retaining ring and remove plug. Save plug in case entire tube is not used. Install static mixing element, replace retaining screw ring, and install tube in gun. Point assembly up and slowly pull the trigger to de-air the mixer. Dispense approximately 1 fluid ounce of material to waste and continue to pump until material is of uniform color with the Part A completely blended with the Part B. Use a putty knife or spatula to ensure adequate coverage and mixing.

For complete instructions on application, please refer to the Series FC22 Plural Component Equipment Recommendations Guide and the Series FC22 Surface Preparation & Application Guide.

THINNING

DO NOT THIN.

PURGE TIME

Less than one minute.

APPLICATION EQUIPMENT

HEATED PLURAL COMPONENT AIRLESS EQUIPMENT ONLY. Please refer to the Series FC22 Plural Component Equipment Recommendations Guide for complete instructions on equipment.

Contact Tnemec Technical Service for equipment recommendations.

Brush: Recommended for small areas, repairs and weld seams.

SURFACE TEMPERATURE

Minimum 35°F (2°C) Maximum 130°F (54°C)

The surface should be dry and at least 5°F (3°C) above the dew point. The coating will not cure below minimum surface temperature. **Note:** Do not apply when humidity exceeds 80%. Dehumidification equipment is recommended if humidity exceeds 80%.

HOLIDAY TESTING

If required by the project specifications, holiday testing should be performed in accordance with NACE SP0188. Refer to the Series FC22 Surface Preparation & Application Guide for voltage recommendations and curing parameters prior to testing.

CLEANUP

Flush and clean all equipment immediately after use with Tnemec No. 4 Thinner. Use No. 74 Thinner when needed to meet local VOC regulations.

WARRANTY & LIMITATION OF SELLER'S LIABILITY: Tnemec Company, Inc. warrants only that its coatings represented herein meet the formulation standards of Tnemec Company, Inc. THE WARRANTY DESCRIBED IN THE ABOVE PARAGRAPH SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. The buyer's sole and exclusive remedy against Tnemec Company, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist and the exclusive remedy shall not have failed its essential purpose as long as Tnemec is willing to provide comparable replacement product to the buyer. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, ENVIRONMENTAL INJURIES OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. Technical and application information herein is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and Tnemec Company makes no claim that these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

Tnemec Company Incorporated 6800 Corporate Drive Kansas City, Missouri 64120-1372 1-800-TNEMEC1 Fax: 1-816-483-3969 www.tnemec.com

Specification 2.1.A.1

Interior Wet Coating System
(Below the Overflow Level)

Sherwin Williams



Protective
&
Marine
Coatings



Certified to
NSF/ANSI 61

COROTHANE® I GALVAPAC 2K ZINC PRIMER

PART A
PART F

B65G10
B69D210

BINDER
ZINC DUST

Revised: November 10, 2016

PRODUCT INFORMATION

5.11

PRODUCT DESCRIPTION

COROTHANE® I GALVAPAC 2K ZINC PRIMER is a two component, moisture curing urethane zinc-rich primer that contains micaceous iron oxide. Designed for low temperature application to blast cleaned or power tool cleaned steel surfaces.

- Low temperature application - down to 20°F (-7°C)
- Easy to apply and recoat
- Resistant to mudcracking
- Abrasion and chemical resistant
- Meets Class B requirements for Slip Coefficient and Creep Resistance, .54
- Enhanced coating strength and edge protection with micaceous iron oxide addition

PRODUCT CHARACTERISTICS

Finish:	Flat
Color:	Gray
Volume Solids:	67% ± 2%, mixed
Weight Solids:	91.7% ± 2%
VOC (calculated):	<340 g/L; 2.8 lb/gal, mixed
Mix Ratio:	2 components; premeasured 2.75 gallon mix

Zinc Content in Dry Film: 83% ± 2% by weight

Recommended Spreading Rate per coat:

	Standard		AWWA*	
	Min	Max	Min	Max
Wet mils (microns)	4.5 (112)	6.8 (170)	3.0 (75)	6.0 (150)
Dry mils (microns)	3.0 (75)	4.0 (100)	2.0 (50)	4.0 (100)
~Coverage sq ft/gal (m ² /L)	268 (6.5)	358 (8.8)	268 (6.5)	536 (13)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1072 (26.2)			

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

*See Recommended Systems on Product Information page

Drying Schedule @ 5.0 mils wet (125 microns):

	@ 40°F/4.5°C	@ 77°F/25°C 50% RH	@ 100°F/38°C
To touch:	45 minutes	20 minutes	10 minutes
To recoat (min.): atmospheric service	8 hours	4-6 hours	1 hour
To recoat (min.): immersion service	24 hours	12 hours	10 hours
To recoat (max.):	12 months	12 months	12 months
To cure: atmospheric service	5 days	3 days	1 day
To cure: immersion service	14 days	7 days	5 days

*If maximum recoat time is exceeded, abrade surface before recoating.
Drying time is temperature, humidity, and film thickness dependent.*

For potable water service, consult www.nsf.org for details on recoat and dry times at indicated temperature. Sterilize and rinse per AWWA C652.

Shelf Life:	Part A - 12 months, unopened Part F - 24 months, unopened Store indoors at 40°F (4.5°C) to 100°F (38°C).
Flash Point:	94°F (34°C), PMCC
Reducer/Clean Up:	Reducer #15, R7K15

RECOMMENDED USES

- **Immersion Service - potable water:**
 - Meets NSF Standard 61 for use in potable water storage.
 - 250,000 gallon untopcoated
 - 20,000 gallon minimum topcoated
- Meets requirements of SSPC Paint Spec No. 40 for zinc rich moisture cure urethane primer
- As a primer in a urethane coating system for bridges, tanks, chemical, and marine structures
- Wind Towers - onshore and offshore
- Ideal for priming water assisted abrasive blasted surfaces where flash rusting or blooming limits the use of conventional zinc rich coatings
- Acceptable for use with cathodic protection with select topcoats
- Conforms to AWWA D102 Inside Coating System #3 (ICS-3), Inside Coating System #4 (ICS-4) Inside Coating System #5 (ICS-5), Outside Coating System #2 (OCS-2), Outside Coating System #3 (OCS-3), Outside Coating System #4 (OCS-4), and Outside Coating System #6 (OCS-6)
- A component of INFINITANK

PERFORMANCE CHARACTERISTICS

Substrate*: Steel

Surface Preparation*: SSPC-SP5

System Tested*:

1 ct. Corothane I GalvaPac 2K Zinc Primer @ 3.5 mils (88 microns) dft

1 ct. Corothane I MIO-Aluminum @ 3.0 mils (75 microns) dft

*unless otherwise noted below

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	45 mg loss
Adhesion (Zinc only)	ASTM D4541	1943 psi
Corrosion Weathering	ASTM D5984, 15 cycles, 5000 hours	Rating 10 per ASTM D610 Rusting (field); Rating 10 per ASTM D714 Blistering
Direct Impact Resistance (Zinc only)	ASTM D2794	160 in. lb.
Dry Heat Resistance	ASTM D2485	300°F (149°C) continuous, 350°F (177°C) intermittent
Flexibility	ASTM D522, 180° bend, 1/4" mandrel	Passes
Immersion (Galvapac/2 cts Macropoxy 646 NSF)	5 year potable water	Rating 10 per ASTM D610 for Rusting; Rating 10 per ASTM D714 for Blistering
Moisture Condensation Resistance (Zinc only)	ASTM D4585, 100°F (38°C), 4000 hours	Rating 10 per ASTM D610 for Rusting; Rating 10 per ASTM D714 for Blistering
Pencil Hardness	ASTM D3363	2H (zinc only)
Salt Fog Resistance (Zinc only)	ASTM B117, 5000 hours	Rating 10 per ASTM D610 for Rusting; Rating 10 per ASTM D714 for Blistering
Slip Coefficient* (Zinc only)	AISC Specification for Structural Joints Using ASTM A325 or ASTM A490 Bolts	Class B, .54
Wet Heat Resistance	Non-immersion	190°F (88°C)

Complies with ISO 12944-5 C5I and C5M requirements.

*Refer to Slip Certification document



Protective
&
Marine
Coatings



Certified to
NSF/ANSI 61

COROTHANE® I GALVAPAC 2K ZINC PRIMER

PART A
PART F

B65G10
B69D210

BINDER
ZINC DUST

Revised: November 10, 2016

PRODUCT INFORMATION

5.11

RECOMMENDED SYSTEMS

	Dry Film Thickness / ct.	
	Mils	(Microns)
Immersion Service, AWWA, Steel:		
*AWWA D102 Inside Coating System No. 3		
minimum AWWA	22.0	(550)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. SherPlate PW Epoxy	20	(500)
*AWWA D102 Inside Coating System No. 4		
minimum AWWA	32.0	(800)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. SherFlex Elastomeric	30	(750)
*AWWA D102 Inside Coating System No. 5		
minimum AWWA	10.0	(250)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
2 cts. Macropoxy 646 PW	4.0	(100)
Immersion Service, Potable Water, Steel:		
1 ct. Corothane I GalvaPac 2K Zinc Primer	3.0-4.0	(75-100)
2 cts. Macropoxy 646 PW	5.0-10.0	(125-250)
Immersion Service (Non-Potable Water), Steel:		
1 ct. Corothane I GalvaPac 2K Zinc Primer	3.0-4.0	(75-100)
2 cts. Corothane I Coal Tar	5.0-7.0	(125-175)
Atmospheric Service, Steel:		
*AWWA D102 Outside Coating System No. 2		
minimum AWWA	6.5	(188)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. Corothane Ironox B	3.0	(75)
1 ct. Corothane I HS	1.5	(40)
*AWWA D102 Outside Coating System No. 3		
minimum AWWA	7.5	(188)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. DTM/SherCryl/SprayLastic	2.0	(50)
1 ct. Corothane I HS	2.0	(50)
*AWWA D102 Outside Coating System No. 4		
minimum AWWA	7.5	(188)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. Acrolon 218HS/HS Polyurethane	3.0	(75)
1 ct. FluoroKem HS	2.0	(50)
*AWWA D102: Outside Coating System No. 6		
minimum AWWA	6.0	(150)
1 ct. Corothane I GalvaPac 2K Zinc Primer	2.0	(50)
1 ct. Macropoxy 646 PW	2.0	(50)
1 ct. Acrolon Ultra/HS Polyurethane	2.0	(50)
Steel, Rapid Return to Service:		
1 ct. Corothane I GalvaPac 2K Zinc Primer	3.0-4.0	(75-100)
1 ct. EnviroLastic 980 PA	6.0-9.0	(150-225)
ISO 12944 C5M System:		
1 ct. Corothane I GalvaPac 2K Zinc Primer	3.0-4.0	(75-100)
1 ct. EnviroLastic 980 PA	6.0-9.0	(150-225)

Acceptable for use over Zinc Clad PCP Ultra. Topcoat required.

The systems listed above are representative of the product's use, other systems may be appropriate.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Iron & Steel
Atmospheric: SSPC-SP6/NACE 3, 2 mil
(50 micron) profile preferred

Immersion, with recommended topcoat:
SSPC-SP10, 2 mil (50 micron) profile

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 3	-
Power Tool Cleaning	C St 3	C St 3	SP 3	-
Pitted & Rusted	D St 3	D St 3	SP 3	-

TINTING

Do not tint.

APPLICATION CONDITIONS

Temperature:
air and surface: 20°F (-7°C) minimum
120°F (49°C) maximum
material: 45°F (7°C) minimum

Do not apply over surface ice

Relative humidity: 30% minimum, 99% maximum

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging:
Part A: 1.73 gallons (6.5L) in a 3 gallon
(11.3L) container
Part F: 60 lb zinc dust, 7.2 Kg/L
Weight: 28.5 ± 0.2 lb/gal, 3.42 Kg/L

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective
&
Marine
Coatings



Certified to
NSF/ANSI 61

COROTHANE® I GALVAPAC 2K ZINC PRIMER

PART A
PART F

B65G10
B69D210

BINDER
ZINC DUST

Revised: November 10, 2016

APPLICATION BULLETIN

5.11

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Iron & Steel (immersion service)

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Remove all weld spatter and round all sharp edges by grinding. Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

Iron & Steel (atmospheric service)

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

APPLICATION CONDITIONS

Temperature:
air and surface: 20°F (-7°C) minimum
120°F (49°C) maximum
material: 45°F (7°C) minimum

Do not apply over surface ice

Relative humidity: 30% minimum, 99% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean UpReducer #15, R7K15

Airless Spray

Pump.....30:1
Pressure.....1800-2000 psi
Hose.....1/4" ID
Tip0.015" - .019"
Filter60 mesh
Reduction.....As needed up to 10% by volume

Conventional Spray

Unit.....	Graco	Binks
Gun	900	95
Fluid Nozzle	070	66/65
Air Nozzle.....	947	63PR
Atomization Pressure.....	60-70 psi	60-70 psi
Fluid Pressure.....	15-20 psi	15-20 psi
Reduction.....	As needed up to 10% by volume	

Brush

Brush.....Natural bristle
Reduction.....As needed up to 10% by volume

Roller

Cover3/8" natural or synthetic with
solvent resistant core
Reduction.....As needed up to 10% by volume

If specific application equipment is not listed above, equivalent equipment may be substituted.

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	Pitted & Rusted	D St 3	SP 3	-



Protective
&
Marine
Coatings



Certified to
NSF/ANSI 61

COROTHANE® I GALVAPAC 2K ZINC PRIMER

PART A
PART F

B65G10
B69D210

BINDER
ZINC DUST

Revised: November 10, 2016

APPLICATION BULLETIN

5.11

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Corothane I - GalvaPac Zinc Primer comes in 2 premeasured containers which when mixed provides 2.75 gallons (10.4L) of ready-to-apply material.

Mixing Instructions: Thoroughly agitate Binder Part A. Using continuous air driven agitation, slowly mix all 60 lbs. of Zinc Dust, B69D210, Part F into Binder Part A until mixture is completely uniform. After mixing, pour mixture through 30-60 mesh screen. Mixed material must be used within 8 hours. Do not mix previously mixed material with new.

If reducer solvent is used, add only after both components have been thoroughly mixed.

Recommended Spreading Rate per coat:

	Standard		AWWA*	
	Min	Max	Min	Max
Wet mils (microns)	4.5 (112)	6.8 (170)	3.0 (75)	6.0 (150)
Dry mils (microns)	3.0 (75)	4.0 (100)	2.0 (50)	4.0 (100)
~Coverage sq ft/gal (m ² /L)	268 (6.5)	358 (8.8)	268 (6.5)	536 (13)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1072 (26.2)			

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

*See Recommended Systems on Product Information page

Drying Schedule @ 5.0 mils wet (125 microns):

	@ 40°F/4.5°C	@ 77°F/25°C	@ 100°F/38°C
	50% RH		
To touch:	45 minutes	20 minutes	10 minutes
To recoat (min.): atmospheric service	8 hours	4-6 hours	1 hour
To recoat (min.): immersion service	24 hours	12 hours	10 hours
To recoat (max.):	12 months	12 months	12 months
To cure: atmospheric service	5 days	3 days	1 day
To cure: immersion service	14 days	7 days	5 days

If maximum recoat time is exceeded, abrade surface before recoating.
Drying time is temperature, humidity, and film thickness dependent.

For potable water service, consult www.nsf.org for details on recoat and dry times at indicated temperature. Sterilize and rinse per AWWA C652.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with Reducer #15, R7K15. Clean tools immediately after use with Reducer #15, R7K15. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, adhesion, and NSF 61 approval.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Reducer #15, R7K15.

Pour a small amount of Reducer #15, R7K15 over the top of the paint in the can to prevent skinning or gelling.

Place a temporary cover over the pail to keep excessive moisture, condensation, fog, or rain from contaminating the coating.

Do not use continuous agitation.

It is recommended that partially used cans not be sealed/closed for use at a later date.

An intermediate coat is recommended to provide a uniform appearance of the topcoat.

Corothane I KA Accelerator is acceptable for use (except NSF applications). See data page 5.98 for details.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective & Marine Coatings



Certified to
NSF/ANSI 61

MACROPOXY® 5500 LOW VOC EPOXY

PART A B58-X740
PART B B58VX740
PART B B58VX745

SERIES
HARDENER
OAP HARDENER

Revised: March 16, 2017

PRODUCT INFORMATION

4.86

PRODUCT DESCRIPTION

MACROPOXY 5500 is a high solids, polyamidoamine epoxy tank lining developed for potable water storage tanks. Superior spray and performance properties make **MACROPOXY 5500** ideal for field or shop applications.

- Low odor, Low VOC
- Outstanding application properties
- Recommended for potable water

PRODUCT CHARACTERISTICS

Finish: Semi-Gloss
Color: Red Primer; White, Light Blue and Beige Topcoats
Volume Solids: 74% ± 2%, mixed
Weight Solids: 82% ± 2%, mixed
VOC (EPA Method 24): <100 g/L; 0.83 lb/gal
Mix Ratio: 1:1 by volume

Primer Recommended Spreading Rate per coat:

B58RX740	Minimum	Maximum
Wet mils (microns)	3.0 (75)	8.0 (200)
Dry mils (microns)	2.0 (50)	6.0 (150)
~Coverage sq ft/gal (m²/L)	197 (4.8)	593 (14.4)
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	1187 (29.1)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Primer Drying Schedule @ 6.0 mils wet (150 microns):

B58RX740	@ 50°F/10°C	@ 77°F/25°C	@ 100°F/38°C
	50% RH		
To touch:	2 hours	1.5 hours	1 hour
To handle:	24 hours	16 hours	5 hours
To recoat:			
minimum:	48 hours	16 hours	5 hours
maximum:	2 months	2 months	7 days
Cure for:			
immersion:	14 days*	7 days	7 days
<i>If maximum recoat time is exceeded, abrade surface before recoating.</i>			
<i>Drying time is temperature, humidity, and film thickness dependent.</i>			
Pot Life:	3 hours	1.5 hours	1 hour
Sweat-in-time:	None	None	None
<i>*For Potable Water Service, allow a minimum of 7 days at/above 77°F (25°C) cure to service. Sterilize and rinse per AWWA C652.</i>			

Topcoats Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	8.0 (200)	18.0 (400)
Dry mils (microns)	6.0 (150)	14.0 (350)
~Coverage sq ft/gal (m²/L)	79 (1.9)	197 (4.8)
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	1187 (29.1)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

PRODUCT CHARACTERISTICS (CONT'D)

Topcoats Drying Schedule @ 10.0 mils wet (250 microns):

	@ 50°F/10°C	@ 77°F/25°C	@ 100°F/38°C
	50% RH		
To touch:	2 hours	1.5 hours	1 hour
To handle:	24 hours	16 hours	5 hours
To recoat:			
minimum:	48 hours	16 hours	5 hours
maximum:	2 months	2 months	7 days
Cure for:			
immersion:	14 days*	7 days	7 days
<i>If maximum recoat time is exceeded, abrade surface before recoating.</i>			
<i>Drying time is temperature, humidity, and film thickness dependent.</i>			
Pot Life:	3 hours	1.5 hours	1 hour
Sweat-in-time:	None	None	None
<i>*For Potable Water Service, allow a minimum of 7 days at/above 77°F (25°C) cure to service. Sterilize and rinse per AWWA C652.</i>			

Shelf Life:	36 months, unopened Store indoors at 40°F (4.5°C) to 100°F (38°C).
Flash Point:	93°F (34°C), Seta Flash, mixed
Reducer/Clean Up:	Reducer R7K111

RECOMMENDED USES

- For potable water service, consult WWW.NSF.ORG
- Water treatment plants
- Complies with AWWA D102 for ICS #1, #2, & #5; for OCS #5 & #6
- Complies with AWWA D102 Meets the requirements of AWWA C210

PERFORMANCE CHARACTERISTICS

Substrate*: Steel

Surface Preparation*: SSPC-SP10/NACE 2

System Tested*:

1 ct. Macropoxy 5500 @ 6.0 mils (150 microns) dft

*unless otherwise noted below

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	120 mg loss
Adhesion	ASTM D4541	>1700 psi
Corrosion Weathering	ASTM D5894, 36 cycles, 12,000 hours	Rating 10 per ASTM D714 for blistering; Rating 9 per ASTM D616 for rusting
Direct Impact Resistance	ASTM D2794	30 in. lb.
Dry Heat Resistance	ASTM D2485	250°F(121°C)
Flexibility	ASTM D522, 180° bend, 1" mandrel	Pass
Humidity Resistance	ASTM D4585, 6000 hours	No blistering, cracking or rusting
Immersion	18 months fresh and salt water	Rating 10 per ASTM D714 for blistering; Rating 10 per ASTM D610 for rusting
Pencil Hardness	ASTM D3363	4H

Epoxy coatings may darken or discolor following application and curing. Above are typical results and should not be construed as a specification.



Protective & Marine Coatings



Certified to
NSF/ANSI 61

MACROPOXY® 5500 LOW VOC EPOXY

PART A B58-X740
PART B B58VX740
PART B B58VX745

SERIES
HARDENER
OAP HARDENER

Revised: March 16, 2017

PRODUCT INFORMATION

4.86

RECOMMENDED SYSTEMS

Dry Film Thickness / ct.
Mils (Microns)

Immersion and Atmospheric:

Ductile Iron Pipe:

Shop Applied:

1-2 cts. Macropoxy 5500 6.0-14.0 (150-350)

Field Applied:

1 ct. Macropoxy 5500 Primer 2.0-6.0 (50-300)

1 ct. Macropoxy 5500 6.0-14.0 (150-350)

or

1-2 cts. Macropoxy 5500 6.0-14.0 (150-350)

Steel:

2-3 cts. Macropoxy 5500 6.0-14.0* (150-350)

or

1 ct. Macropoxy 5500 Primer 2.0-6.0 (50-150)

1-3 cts. Macropoxy 5500 6.0-14.0* (150-350)

Concrete:

2-3 cts. Macropoxy 5500 6.0-14.0* (150-350)

or

1 ct. Macropoxy 5500 Primer 2.0-6.0 (50-150)

1-3 cts. Macropoxy 5500 6.0-14.0* (150-350)

Potable Water, Immersion, Steel:

*AWWA D102: Inside Coating System No. 1

minimum AWWA 8.0 (200)

1 ct. Macropoxy 5500 3.0 (75)

1 ct. Macropoxy 5500 5.0 (125)

*AWWA D102: Inside Coating System No. 2

minimum AWWA 12.0 (300)

1 ct. Macropoxy 5500 3.0 (75)

1 ct. Macropoxy 5500 4.0 (100)

1 ct. Macropoxy 5500 5.0 (125)

AWWA D012: Inside Coating System No. 3

1ct. Macropoxy 5500 Primer 2.0 mils (50)

1ct. SherPlate PW 20.0 mils (500)

AWWA D102: Inside Coating System No. 4

1ct. Macropoxy 5500 Primer 2.0 mils (50)

1ct. SherFlex S 30.0 mils (750)

AWWA D102: Inside Coating System No. 5

1ct. Corothane I Galvacap Zinc 2.0 mils (50)

1ct. Macropoxy 5500 4.0 mils (100)

1ct. Macropoxy 5500 4.0 mils (100)

Acceptable for use with AWWA D102: Component of Outside Coating System No. 5 and No. 6

Other acceptable topcoats over Macropoxy 5500 Primer:

Dura-Plate UHS

*Maximum of 28.0 mils (700 microns) for entire system

The systems listed above are representative of the product's use, other systems may be appropriate.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Iron & Steel:

Atmospheric: SSPC-SP2/3

Immersion: SSPC-SP10/NACE 2, 2-4 mil
(50-100 micron) profile

Ductile Iron Pipe: NAPF 500.03.03

Concrete:

Atmospheric: SSPC-SP13/NACE 6 with an ICRI CSP 2-4

Immersion: SSPC-SP13/NACE 6 with an ICRI CSP 2-4

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	SSPC	NACE
White Metal	Sa 3	SP 5	1
Near White Metal	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	SP 2	-
Rusted	D St 2	SP 2	-
Pitted & Rusted	D St 2	SP 2	-
Power Tool Cleaning	C St 3	SP 3	-
Rusted	C St 3	SP 3	-
Pitted & Rusted	D St 3	SP 3	-

TINTING

Do not tint.

APPLICATION CONDITIONS

Air, surface, and material temperature: 50°F (10°C) minimum
100°F (38°C) maximum

Surface temp: At least 5°F (2.8°C) above dew point

Relative Humidity: 85% maximum. At least 5°F (2.8°C) above dew point

ORDERING INFORMATION

Packaging:

Part A: 1 gallon (3.78L) and 5 gallon (18.9L)
containers

Part B: 1 gallon (3.78L) and 5 gallon (18.9L)
containers

Weight: 13.3 ± 0.2 lb/gal ; 1.6 Kg/L, mixed, may
vary by color

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective & Marine Coatings



Certified to
NSF/ANSI 61

MACROPOXY® 5500 LOW VOC EPOXY

PART A B58-X740
PART B B58VX740
PART B B58VX745

SERIES
HARDENER
OAP HARDENER

Revised: March 16, 2017

APPLICATION BULLETIN

4.86

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Carbon Steel, Immersion Service:

The surface shall be abrasive blasted to SSPC-SP10/NACE No. 2 Near-White Blast Cleaning with a 2-4 mil (50-100 micron) profile. The anchor profile shall be sharp with no evidence of a peen surface. The finished surface shall be free of all visible oil, grease, dust, dirt, mill scale, rust, coating, oxides, corrosion products, and other foreign matter with no more than 5% staining. After blasting, all dust and loose residue should be removed from the surface by acceptable means. Coat steel the same day as it is prepared and prior to the formation of rust.

Iron & Steel: Minimum surface preparation is Hand Tool Clean per SSPC-SP2. Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6/NACE 3, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils / 50 microns). Prime any bare steel within 8 hours or before flash rusting occurs.

Ductile Iron Pipe: Minimum surface preparation is Power Tool Clean per NAF 500.03.02. Remove all oil and grease from surface by Solvent Cleaning per NAF 500.03.01. For better performance, use Blast Cleaning per NAF 500.03.03, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile. Prime any bare DIP before flash rusting occurs.

Ductile Iron, Immersion Service:

Refer to National Association of Pipe Fabricators Surface Preparations Standard NAF 500-03 as follows:

- NAF 500-03-01 "Solvent Cleaning"
- NAF 500-03-02 "Hand Tool Cleaning"
- NAF 500-03-03 "Power Tool Cleaning"
- NAF 500-03-04 "Abrasive Blast Cleaning of Ductile Iron Pipe"

Concrete and Masonry

For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI No. 310.2R,

CSP 1-3. Surfaces should be thoroughly clean and dry. Concrete and mortar

must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar

and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with Steel-Seam FT910. Follow the standard methods listed below when applicable:

ASTM D4258 Standard Practice for Cleaning Concrete.

ASTM D4259 Standard Practice for Abrading Concrete.

ASTM D4260 Standard Practice for Etching Concrete.

ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete.

SSPC-SP 13/Nace 6 Surface Preparation of Concrete.

ICRI No. 310.2R Concrete Surface Preparation.

Concrete, Immersion Service:

For surface preparation, refer to SSPC-SP13/NACE 6, Section 4.3.1 or 1.3.2 or ICRI No. 310.2R, CSP 1-3.

Surface Preparation Standards

	Condition of Surface	ISO 8501-1 BS7099:A1	SSPC	NACE
White Metal		Sa 3	SP 5	1
Near White Metal		Sa 2.5	SP 10	2
Commercial Blast		Sa 2	SP 6	3
Brush-Off Blast		Sa 1	SP 7	4
Hand Tool Cleaning	Rusted	C St 2	SP 2	-
	Pitted & Rusted	D St 2	SP 2	-
Power Tool Cleaning	Rusted	C St 3	SP 3	-
	Pitted & Rusted	D St 3	SP 3	-

APPLICATION CONDITIONS

Air, surface, and material temperature: 50°F (10°C) minimum
100°F (38°C) maximum

Surface temp: At least 5°F (2.8°C) above dew point

Relative Humidity: 85% maximum. At least 5°F (2.8°C) above dew point

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reducer/Clean UpReducer R7K111

Airless Spray

Pressure.....2700-3000 psi
Hose.....3/8" ID with 1/4" whip
Tip519-525
Filternone
Reduction.....As needed up to 10% by volume

Brush

Brush.....Nylon/Polyester or Natural Bristle
Reduction.....As needed up to 10% by volume

Roller

Cover3/8" woven with solvent resistant core
Reduction.....As needed up to 10% by volume

If specific application equipment is not listed above, equivalent equipment may be substituted.



Protective & Marine Coatings



Certified to
NSF/ANSI 61

MACROPOXY® 5500 LOW VOC EPOXY

PART A B58-X740
PART B B58VX740
PART B B58VX745

SERIES
HARDENER
OAP HARDENER

Revised: March 16, 2017

APPLICATION BULLETIN

4.86

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mix contents of each component thoroughly with low speed power agitation. Make certain no pigment remains on the bottom of the can. Then combine one part by volume of Part A with one part by volume of Part B. Thoroughly agitate the mixture with power agitation.

If reducer solvent is used, add only after both components have been thoroughly mixed.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Primer Recommended Spreading Rate per coat:

B58RX740	Minimum	Maximum
Wet mils (microns)	3.0 (75)	8.0 (200)
Dry mils (microns)	2.0 (50)	6.0 (150)
~Coverage sq ft/gal (m ² /L)	197 (4.8)	593 (14.4)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1187 (29.1)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Primer Drying Schedule @ 6.0 mils wet (150 microns):

B58RX740	@ 50°F/10°C	@ 77°F/25°C	@ 100°F/38°C
		50% RH	
To touch:	2 hours	1.5 hours	1 hour
To handle:	24 hours	16 hours	5 hours
To recoat:			
minimum:	48 hours	16 hours	5 hours
maximum:	2 months	2 months	7 days
Cure for:			
immersion:	14 days*	7 days	7 days

If maximum recoat time is exceeded, abrade surface before recoating.

Drying time is temperature, humidity, and film thickness dependent.

Pot Life: 3 hours 1.5 hours 1 hour

Sweat-in-time: None None None

*For Potable Water Service, allow a minimum of 7 days at/above 77°F (25°C) cure to service. Sterilize and rinse per AWWA C652.

Topcoats Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	8.0 (200)	18.0 (400)
Dry mils (microns)	6.0 (150)	14.0 (350)
~Coverage sq ft/gal (m ² /L)	79 (1.9)	197 (4.8)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1187 (29.1)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Topcoats Drying Schedule @ 10.0 mils wet (250 microns):

	@ 50°F/10°C	@ 77°F/25°C	@ 100°F/38°C
		50% RH	
To touch:	2 hours	1.5 hours	1 hour
To handle:	24 hours	16 hours	5 hours
To recoat:			
minimum:	48 hours	16 hours	5 hours
maximum:	2 months	2 months	7 days
Cure for:			
immersion:	14 days*	7 days	7 days

If maximum recoat time is exceeded, abrade surface before recoating.

Drying time is temperature, humidity, and film thickness dependent.

Pot Life: 3 hours 1.5 hours 1 hour

Sweat-in-time: None None None

*For Potable Water Service, allow a minimum of 7 days cure to service. Sterilize and rinse per AWWA C652.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with R7K111. Clean tools immediately after use with R7K111. Follow manufacturer's safety recommendations when using any solvent.

PERFORMANCE TIPS

Note: Once maximum pot life is exceeded, product may be sprayable but will not hold sag.

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, over thinning, climatic conditions, and excessive film build.

Excessive reduction of material can affect film build, appearance, and adhesion.

Do not mix previously catalyzed material with new.

Do not apply the material beyond recommended pot life.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Reducer R7K111.

Tinting is not recommended for immersion service.

Do not use Quik-Kick Epoxy Accelerator.

Insufficient ventilation, incomplete mixing, miscatalyzation, and external heaters may cause premature yellowing.

Excessive film build, poor ventilation, and cool temperatures may cause solvent entrapment. Avoid entrapment by following the recommended application procedures.

For Immersion Service: Electrical holiday inspection should be performed in accordance with NACE SP0188 "Discontinuity (Holiday) Testing of Protective Coatings" or ASTM D 5162-91 "Standard Practice for Discontinuity (Holiday) Testing of Non-conductive Protective Coating of Metallic Substrates."

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective
&
Marine
Coatings



SHERPLATE PW EPOXY

WITH OPTI-CHECK OAP TECHNOLOGY

PART A	B62W260	WHITE
PART A	B62L260	BLUE
PART B	B62V260	HARDENER
PART B	B62V265	OAP HARDENER

Revised: June 18, 2015

PRODUCT INFORMATION

4.82

PRODUCT DESCRIPTION

SherPlate PW Epoxy is an edge retentive, ultra high solids epoxy amine coating engineered for immersion service in potable water pipes and storage tanks. The rapid return to service and high build, edge retentive properties of this coating provide superior protection.

- One or two coat protection
- Fast return to service
- Low VOC
- Low odor
- Dry to walk-on within four hours
- Designed for plural-component application equipment
- Greater than 70% edge build retention
- NSF approved to standard 61 for potable water (tanks of 25 gallons or greater and pipes of 6" diameter or greater)

PRODUCT CHARACTERISTICS

Finish: Gloss

Color: White-Base and Blue (OAP Hardener can be used with either color)

Volume Solids: 98% ± 2%, mixed

Weight Solids: 98% ± 2%, mixed

VOC (EPA method #24): <85 g/L; 0.71 lb/gal, mixed

Mix Ratio: 1:1 by volume

Recommended Spreading Rate per coat:

	Minimum	Maximum
Tank Lining mils (microns)	16.0 (400)	50.0 (1250)
Pipe Lining mils (microns)	16.0 (400)	50.0 (1250)
~Coverage sq ft/gal (m ² /L)	98 (2.4)	31 (0.8)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1572 (38.5)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 20.0-50.0 mils wet (500-1250 microns):

@ 40°F/4.5°C @ 77°F/25°C @ 100°F/38°C

		50% RH	
To touch:	6 hours	1 hour	35 minutes
To handle:	8-12 hours	3 hours	55 minutes
To recoat:			
minimum:	6 hours	1 hour	35 minutes
maximum:	14 days	14 days	14 days
Foot traffic:	8-12 hours	3 hours	1 hour
To cure:	36 hours	24 hours	12 hours

If maximum recoat time is exceeded, abrade surface before recoating.

Drying time is temperature, humidity, and film thickness dependent.

Sterilize and rinse per AWWA C652.

Pot Life: 7 minutes

Sweat-in-Time: None required

Shelf Life: 24 months
Store indoors at 40°F (4.5°C) to 100°F (38°C).

Flash Point: 230°F (110°C), PMCC, mixed

Reducer: Not recommended

Clean Up: MEK (R6K10) or Reducer R7K104

RECOMMENDED USES

For use over prepared steel or masonry surfaces for water including potable water.

- Where rapid return to service and edge protection film build properties are required
- Part B Hardener available with OAP (optically active pigment)
- Meets or exceeds the requirements of AWWA C210
- Meets or exceeds AWWA D102
- A component of INFINITANK
- Suitable for use in the Mining & Minerals Industry
- Meets MIL-PRF-23236, Type VII, Class 9/18 requirements for single coat application in potable water tanks
- Refer to www.nsf.org website for allowable tank size listing

PERFORMANCE CHARACTERISTICS

System Tested:

1 ct. SherPlate PW Epoxy @ 30.0 mils (750 microns) dft

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060	22.4 mg loss
Adhesion	ASTM D4541	>1,000 psi
Cathodic Disbondment	ASTM G8	Passes AWWA C210 requirements
Elongation	ASTM D638	3.3%
Flexibility	ASTM D522	1/2" (24 hour cure)
Flexural Modulus	ASTM D790	2560 psi
Flexural Strength	ASTM D790	7458 psi
Moisture Condensation Resistance	ASTM D4585, 2000 hours	Passes
Pencil Hardness	ASTM D3363	H
Shore D Hardness	ASTM D2240	83

Immersion (ambient temperature) for the following:

- Fresh Water..... Recommended
- Potable Water..... Recommended
- Salt Water..... Recommended
- 1% Solution of Sodium Hypochlorite..... Recommended
- AWWA C210 Chemical Solutions..... Recommended

Epoxy coatings may darken or yellow after application and curing.



Protective & Marine Coatings



SHERPLATE PW EPOXY

WITH OPTI-CHECK OAP TECHNOLOGY

PART A	B62W260	WHITE
PART A	B62L260	BLUE
PART B	B62V260	HARDENER
PART B	B62V265	OAP HARDENER

Revised: June 18, 2015

PRODUCT INFORMATION

4.82

RECOMMENDED SYSTEMS

	Dry Film Thickness / ct.
	Mils (Microns)
Steel, Immersion (AWWA C210):	
1-2 cts. SherPlate PW Epoxy	16.0-50.0 (400-1250)
Steel, Immersion (AWWA D102):	
1 ct. Optional Primer	*
1-2 cts. SherPlate PW Epoxy	20.0-50.0 (500-1250)
Concrete, Immersion:	
1 ct. Primer	**
1-2 cts. SherPlate PW Epoxy	20.0-50.0 (500-1250)
Steel, Atmospheric:	
1-2 cts. SherPlate PW Epoxy	20.0-50.0 (500-1250)

*Acceptable Primers for Steel:

Macropoxy 5500 Primer
Corothane I Gavapac 1K Zinc Primer
Corothane I Galvapac 2K Zinc Primer
Zinc Clad PCP Ultra

**Acceptable Primers for Concrete:

Copoxy Shop Primer
Corobond 100
Corobond HS
Corobond LT
Dura-Plate 235
Dura-Plate UHS Primer

The systems listed above are representative of the product's use, other systems may be appropriate.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product Application Bulletin for detailed surface preparation information.

Minimum recommended surface preparation:

Iron & Steel:	
Atmospheric:	SSPC-SP6/NACE 3, 2 mil (50 micron) profile or SSPC-SP12/NACE No. 5, WJ-3/SC-2
Immersion:	SSPC-SP10/NACE 2, 2-3 mil (50-75 micron) profile or SSPC-SP12/NACE No. 5, WJ-2/SC-2
Concrete & Masonry:	
Atmospheric:	SSPC-SP13/NACE 6, or ICRI 03732 CSP2-4
Immersion:	SSPC-SP13/NACE 6-4.3.1 or 4.3.2, or ICRI 03732 CSP2-4

Surface Preparation Standards

Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 6	3
Brush-Off Blast	Sa 1	Sa 1	SP 7	4
Hand Tool Cleaning	C St 2	C St 2	SP 2	-
Rusted	D St 2	D St 2	SP 2	-
Pitted & Rusted	D St 2	D St 2	SP 2	-
Power Tool Cleaning	C St 3	C St 3	SP 3	-
Rusted	D St 3	D St 3	SP 3	-
Pitted & Rusted	D St 3	D St 3	SP 3	-

TINTING

Do not tint.

APPLICATION CONDITIONS

Temperature:
air and surface: 40°F (4.5°C) minimum, 110°F (43°C) maximum

For application at 35°F (1.7°C) to 40°F (4.5°C), specific guidelines are required:

- Air & Surface temperature conditions must be expected to remain stable or improve for a period of four hours
- Environmental controls (dehumidification, heating, forced-air ventilation) are recommended to maintain acceptable application conditions
- For Potable Water Service, allow a minimum cure time of 24 hours at 77°F (25°C) prior to placing in service

Relative humidity: 85% maximum

Refer to product Application Bulletin for detailed application information.

ORDERING INFORMATION

Packaging	
Part A:	5 gallon (18.9L) container
Part B:	5 gallon (18.9L) container
Weight:	11.71 ± 0.3 lb/gal ; 1.4 Kg/L, mixed

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.



Protective & Marine Coatings



SHERPLATE PW EPOXY

WITH OPTI-CHECK OAP TECHNOLOGY

PART A	B62W260	WHITE
PART A	B62L260	BLUE
PART B	B62V260	HARDENER
PART B	B62V265	OAP HARDENER

Revised: June 18, 2015

APPLICATION BULLETIN

4.82

SURFACE PREPARATIONS

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Iron & Steel (atmospheric service)

Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3 or SSPC-SP12/NACE No. 5. For surfaces prepared by SSPC SP6/NACE 3, first remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2-3 mils / 50-75 microns). For surfaces prepared by SSPC-SP12/NACE No. 5, all surfaces shall be cleaned in accordance with WJ-3/SC2. Pre-existing profile should be approximately 2 mils (50 microns). Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

Iron & Steel (immersion service)

Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2, or SSPC-SP12/NACE No. 5. For SSPC-SP10/NACE 2, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2-3 mils / 50-75 microns). For SSPC-SP12/NACE No.5, all surfaces to be coated shall be cleaned in accordance with WJ-2/SC2 standards. Pre-existing profile should be approximately 2 mils (50 microns). Remove all weld spatter. Prime any bare steel the same day as it is cleaned or before flash rusting occurs.

Concrete and Masonry

For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI No. 310.2R, CSP 2-3. Surfaces should be thoroughly clean and dry. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with Steel-Seam FT910. Primer required. For surface preparation of Concrete, Immersion Service, refer to SSPC-SP13/NACE 6, Section 4.3.1 or 1.3.2 or ICRI No. 310.2R, CSP 2-3.

Follow the standard methods listed below when applicable:

ASTM D4258 Standard Practice for Cleaning Concrete.
ASTM D4259 Standard Practice for Abrading Concrete.
ASTM D4260 Standard Practice for Etching Concrete.
ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete.
SSPC-SP 13/Nace 6 Surface Preparation of Concrete.
ICRI No. 310.2R Concrete Surface Preparation.

Surface Preparation Standards				
Condition of Surface	ISO 8501-1 BS7079:A1	Swedish Std. SIS055900	SSPC	NACE
White Metal	Sa 3	Sa 3	SP 5	1
Near White Metal	Sa 2.5	Sa 2.5	SP 10	2
Commercial Blast	Sa 2	Sa 2	SP 40	3
Brush-Off Blast	Sa 1	Sa 1	SP 4	4
Hand Tool Cleaning	C St 2	C St 2	SP 3	-
Rusted	D St 2	D St 2	SP 3	-
Pitted & Rusted	D St 3	D St 3	SP 3	-
Rusted	C St 3	C St 3	SP 3	-
Power Tool Cleaning	D St 3	D St 3	SP 3	-
Pitted & Rusted	D St 3	D St 3	SP 3	-

APPLICATION CONDITIONS

Temperature:
air and surface: 40°F (4.5°C) minimum, 110°F (43°C) maximum

For application at 35°F (1.7°C) to 40°F (4.5°C), specific guidelines are required:

- Air & Surface temperature conditions must be expected to remain stable or improve for a period of four hours
- Environmental controls (dehumidification, heating, forced-air ventilation) are recommended to maintain acceptable application conditions
- For Potable Water Service, allow a minimum cure time of 24 hours at 77°F (25°C) prior to placing in service

The material should be 85°F-130°F / 29°C-54°C (vary as needed) at the mixing block for optimal atomization based on tip size and pump pressure. **Do not heat above 140°F (60°C).**

Relative humidity: 85% maximum

APPLICATION EQUIPMENT

The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.

Reduction Not recommended
Clean Up MEK (R6K10) or R7K104

Plural Component Equipment:

Pump WIWA DUOMIX 1:1, Graco Extreme Mix, or Graco XP70
Pressure 4000 psi
Hose 3/8" ID
Tip021" - .025"
Pump heater setting 110°F-130°F (43°C-54°C)*
Material temperature
at gun tip 110°F-130°F (43°C-54°C), vary as needed

Brush For stripe coating and repair only
Brush Nylon/Polyester or Natural Bristle

Roller For stripe coating and repair only
Cover 3/8" woven with solvent resistant core

*Material should be preheated to 110°F (43°C) prior to spraying.

If specific application equipment is not listed above, equivalent equipment may be substituted.



Protective & Marine Coatings



SHERPLATE PW EPOXY WITH OPTI-CHECK OAP TECHNOLOGY

PART A	B62W260	WHITE
PART A	B62L260	BLUE
PART B	B62V260	HARDENER
PART B	B62V265	OAP HARDENER

Revised: June 18, 2015

APPLICATION BULLETIN

4.82

APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mixing Instructions: Mix contents of each component thoroughly using low speed power agitation. Make certain no pigment remains on the bottom or the sides of the can. Then combine one part by volume of Part A with one part by volume of Part B. Thoroughly agitate the mixture with power agitation.

To ensure that no unmixed material remains on the sides or bottom of the cans after mixing, visually observe the container by pouring the material into a separate container.

Apply paint at the recommended film thickness and spreading rate as indicated below:

Recommended Spreading Rate per coat:

	Minimum	Maximum
Tank Lining mils (microns)	16.0 (400)	50.0 (1250)
Pipe Lining mils (microns)	16.0 (400)	50.0 (1250)
~Coverage sq ft/gal (m ² /L)	98 (2.4)	31 (0.8)
Theoretical coverage sq ft/gal (m ² /L) @ 1 mil / 25 microns dft	1572 (38.5)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 20.0-50.0 mils wet (500-1250 microns):

	@ 40°F/4.5°C	@ 77°F/25°C 50% RH	@ 100°F/38°C
To touch:	6 hours	1 hour	35 minutes
To handle:	8-12 hours	3 hours	55 minutes
To recoat:			
minimum:	6 hours	1 hour	35 minutes
maximum:	14 days	14 days	14 days
Foot traffic:	8-12 hours	3 hours	1 hour
To cure:	36 hours	24 hours	12 hours

If maximum recoat time is exceeded, abrade surface before recoating.

Drying time is temperature, humidity, and film thickness dependent.

Sterilize and rinse per AWWA C652.

Pot Life:	7 minutes
Sweat-in-Time:	None required

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

CLEAN UP INSTRUCTIONS

Clean spills and spatters immediately with MEK, R6K10. Clean tools immediately after use with MEK, R6K10. Follow manufacturer's safety recommendations when using any solvent.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

PERFORMANCE TIPS

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross-coat spray at a right angle.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

No reduction of material is recommended as this can affect film build, appearance, and adhesion.

Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.

Do not mix previously catalyzed material with new.

Do not apply the material beyond recommended pot life.

Remove and solvent clean tip housing every 20-30 minutes.

For Immersion Service: (if required) Holiday test in accordance with NACE SP0188.

OAP fluorescent pigment can be used as a one or two coat system. When using OAP in a two coat system, use OAP hardener in first coat.

Refer to Product Information sheet for additional performance characteristics and properties.

SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.