



Please Reply To:

**AmeriSci New York**

117 EAST 30TH ST.  
NEW YORK, NY 10016  
TEL: (212) 679-8600 • FAX: (212) 679-3114

**FACSIMILE TELECOPY TRANSMISSION**

**To:** Michael Delaney  
Mabbett & Associates, Inc.

**Fax #:**

**Email:** delaney@mabbett.com

**From:** Marik Peysakhov  
**AmeriSci Job #:** 211093578  
**Subject:** ELAP-PLM/TEM 5 day Results  
**Client Project:** 20100009.004; VISN 2 - Bath;  
Building 86

**Date:** Monday, September 26, 2011

**Time:** 12:23:59

**Comments:**

**Number of Pages:** 5  
(including cover sheet)

CONFIDENTIALITY NOTICE: Unless otherwise indicated, the information contained in this communication is confidential information intended for use of the individual named above. If the reader of this communication is not the intended recipient, you are hereby notified that any dissemination, distribution or copying of this communication is prohibited. If you have received this communication in error, please immediately notify the sender by telephone and return the original message to the above address via the US Postal Service at our expense. Preliminary data reported here will be verified before final report is issued. Samples are disposed of in 60 days or unless otherwise instructed by the protocol or special instructions in writing. Thank you.

**Certified Analysis    Service 24 Hours A Day • 7 Days A Week    Competitive Prices**  
visit our web site - [www.amerisci.com](http://www.amerisci.com)

**Boston • Los Angeles • New York • Richmond**

**AmeriSci New York**117 EAST 30TH ST.  
NEW YORK, NY 10016

TEL: (212) 679-8600 • FAX: (212) 679-3114

**PLM Bulk Asbestos Report**Mabbett & Associates, Inc.  
Attn: Michael Delaney  
5 Alfred Circle  
  
Bedford, MA 01730**Date Received** 09/21/11    **AmeriSci Job #** 211093578  
**Date Examined** 09/25/11    **P.O. #**  
**ELAP #** 11480    **Page** 1 of 2  
**RE:** 20100009.004; VISN 2 - Bath; Building 86

Client No. / HGA	Lab No.	Asbestos Present	Total % Asbestos
01A 1	211093578-01 <b>Location:</b> Exterior - Loading Dock - Electric Wire Insulation - Black	<b>No</b>	NAD (by NYS ELAP 198.6) by John A. Burns on 09/25/11
<b>Analyst Description:</b> Black, Homogeneous, Non-Fibrous, Bulk Material <b>Asbestos Types:</b> <b>Other Material:</b> Non-fibrous 0.6 %			
01B 1	211093578-02 <b>Location:</b> Exterior - Loading Dock - Electric Wire Insulation - Black	<b>No</b>	NAD (by NYS ELAP 198.6) by John A. Burns on 09/25/11
<b>Analyst Description:</b> Black, Homogeneous, Non-Fibrous, Bulk Material <b>Asbestos Types:</b> <b>Other Material:</b> Non-fibrous 0.8 %			
02A 2	211093578-03 <b>Location:</b> Exterior - Loading Dock - Door Frame Caulk	<b>Yes</b>	5 % (by NYS ELAP 198.6) by John A. Burns on 09/25/11
<b>Analyst Description:</b> Grey, Homogeneous, Non-Fibrous, Bulk Material <b>Asbestos Types:</b> Chrysotile 5.0 % <b>Other Material:</b> Fibrous Talc Trace, Non-fibrous 61.9 %			
02B 2	211093578-04 <b>Location:</b> Exterior - Loading Dock - Door Frame Caulk		NA/PS
<b>Analyst Description:</b> Bulk Material <b>Asbestos Types:</b> <b>Other Material:</b>			
03A 3	211093578-05 <b>Location:</b> Exterior - South Wall - Window Glazing Compound	<b>No</b>	NAD (by NYS ELAP 198.6) by John A. Burns on 09/25/11
<b>Analyst Description:</b> Grey, Homogeneous, Non-Fibrous, Bulk Material <b>Asbestos Types:</b> <b>Other Material:</b> Non-fibrous 3.2 %			

Client Name: Mabbett &amp; Associates, Inc.

**PLM Bulk Asbestos Report**

20100009.004; VISN 2 - Bath; Building 86

Client No. / HGA	Lab No.	Asbestos Present	Total % Asbestos
03B 3	211093578-06 Location: Exterior - South Wall - Window Glazing Compound	Yes	1.7 % (by NYS ELAP 198.6) by John A. Burns on 09/25/11
Analyst Description: Grey, Homogeneous, Non-Fibrous, Bulk Material Asbestos Types: Chrysotile 1.7 % Other Material: Non-fibrous 11.8 %			
03C 3	211093578-07 Location: Exterior - South Wall - Window Glazing Compound		NA/PS
Analyst Description: Bulk Material Asbestos Types: Other Material:			

**Reporting Notes:**

Analyzed by: John A. Burns

\*NAD/NSD = no asbestos detected; NA = not analyzed; NA/PS = not analyzed/positive stop; PLM Bulk Asbestos Analysis by EPA 600/M4-82-020 per 40 CFR 763 (NVLAP Lab Code 200546-0), ELAP PLM Method 198.1 for NY friable samples or 198.6 for NOB samples (NY ELAP Lab ID11480);

Note: PLM is not consistently reliable in detecting asbestos in floor coverings and similar non-friable organically bound materials. NAD or Trace results by PLM are inconclusive, TEM is currently the only method that can be used to determine if this material can be considered or treated as non asbestos-containing in NY State (also see EPA Advisory for floor tile, FR 59,146,38970,8/1/94) National Institute of Standards and Technology Accreditation requirements mandate that this report must not be reproduced except in full without the approval of the lab. This PLM report relates ONLY to the items tested. AIHA Lab # 102843, RI Cert#AAL-094, CT Cert#PH-0186, Mass Cert#AA000054.

Reviewed By: \_\_\_\_\_ END OF REPORT \_\_\_\_\_

Client Name: Mabbett &amp; Associates, Inc.

**Table I**  
**Summary of Bulk Asbestos Analysis Results**

20100009.004; VISN 2 - Bath; Building 86

AmeriSci Sample #	Client Sample#	HG Area	Sample Weight (gram)	Heat Sensitive Organic %	Acid Soluble Inorganic %	Insoluble Non-Asbestos Inorganic %	** Asbestos % by PLM/DS	** Asbestos % by TEM
01	01A	1	0.173	97.7	1.7	0.6	NAD	NAD
Location:	Exterior - Loading Dock - Electric Wire Insulation - Black							
02	01B	1	0.129	99.2	0.0	0.8	NAD	NAD
Location:	Exterior - Loading Dock - Electric Wire Insulation - Black							
03	02A	2	0.269	25.7	7.4	61.9	Chrysotile 5.0	NA
Location:	Exterior - Loading Dock - Door Frame Caulk							
04	02B	2	0.147	25.9	10.2	63.9	NA/PS	NA
Location:	Exterior - Loading Dock - Door Frame Caulk							
05	03A	3	0.309	8.4	88.3	3.2	NAD	NA
Location:	Exterior - South Wall - Window Glazing Compound							
06	03B	3	0.326	10.1	76.4	11.8	Chrysotile 1.7	NA
Location:	Exterior - South Wall - Window Glazing Compound							
07	03C	3	0.269	6.7	77.7	15.6	NA/PS	NA
Location:	Exterior - South Wall - Window Glazing Compound							

Analyzed by: Marik Peysakhov; Date Analyzed 9/26/2011

\*\*Quantitative Analysis (Semi/Full); Bulk Asbestos Analysis - PLM by EPA 600/M4-82-020 per 40 CFR or ELAP 198.1 for New York friable samples or ELAP 198.6 for New York NOB samples; TEM (Semi/Full) by EPA 600/R-93/116 (not covered by NVLAP Bulk accreditation) or ELAP 198.4; for New York samples; NAD = no asbestos detected during a quantitative analysis; NA = not analyzed; Trace = <1%; Quantitation for beginning weights of <0.1 grams should be considered as qualitative only; Qualitative Analysis: Asbestos analysis results of "Present" or "NVA = No Visible Asbestos" represents results for Qualitative PLM or TEM Analysis only (no accreditation coverage available from any regulatory agency for qualitative analyses); AIHA Lab # 102843, NVLAP Lab Code 200546-0, NYSDOH ELAP Lab ID#11480.

Warning Note: PLM limitation, only TEM will resolve fibers <0.25 micrometers in diameter. TEM bulk analysis is representative of the fine grained matrix material and may not be representative of non-uniformly dispersed debris for which PLM evaluation is recommended (i.e. soils and other heterogeneous materials).



Reviewed By: \_\_\_\_\_



**Phone/FAX:** 781-275-6050 / 781-275-5651

Requested Turn Around Time: 5 Day

\*Samples identified with a homogeneous sampling group (HSG) number are categorized with "Positive Stop" analysis. Perform sequential analysis on each HSG until > 1% asbestos content detected; do not analyze any of the next samples in the HSG. Samples marked HOLD are to be set aside until further notice.

Chain of Custody	Signature	Company Name / Air Bill No.	Date	Time
Relinquished By:		O'Brien & Gere	9/20/11	0900
Relinquished By:	FEDEX			
Relinquished By:				
Received By:			9/21	1146